

ACEMATT® OK 412

Characteristic physico-chemical data*)

Properties and test methods	Unit	Value
Loss on drying 2 h at 105°C following ISO 787-2	%	≤ 6
pH value 5 % in water following ISO 787-9	-	6.3
Sulfate content following ISO 19350	%	≤ 1
Particle size, d50 Laser diffraction following ISO 13320	µm	6.3
Carbon content elemental analyser LECO following ISO 3262-19	%	5.5
Specific surface area (N ₂) Multipoint following ISO 9277	m ² /g	130
DOA absorption following ISO 19246	ml/100g	240
SiO ₂ content ¹⁾ following ISO 3262-19	%	≥ 98

1) based on ignited substance
*) The given data are typical values.
Specifications on request.

Registrations

ACEMATT® OK 412

CAS-No.	112926-00-8 (ex 7631-86-9) 9002-88-4
EINECS (Europe)	registered
TSCA (USA)	registered
DSL (Canada)	registered
AICS (Australia)	registered
KECI (Korea)	registered
ENCS (Japan)	registered
PICCS (Philippines)	registered
IECS (China)	registered
NZIoC (New Zealand)	registered

ACEMATT® Matting agents are high performance silica developed for a variety of applications in Paints & Coatings.

ACEMATT® OK 412 is a fine-grained wax after-treated precipitated silica. This effective matting agent is suitable for pigmented coatings and due to the remarkable suspension behaviour it is particularly suitable for clear coatings and other non-pigmented systems.

Properties and applications

The physical properties of ACEMATT® OK 412 make it an all-purpose matting agent for coatings and overprint varnishes.

Safety and handling

Information concerning the safety of this product is listed in the corresponding Safety Data Sheet, which will be sent with the first delivery or upon updating. Such information is also available from: Evonik Resource Efficiency GmbH, Product Safety Department, E-Mail: sds-hu@evonik.com. We recommend to read carefully the material safety data sheet prior to the use of our product.

Packaging and storage

For details regarding our packaging options for this product, please contact your local sales representative.

Our products are inert and extremely stable chemically. However, due to their high specific surface area, they can absorb moisture and volatile organic compounds from the surrounding atmosphere. Therefore, we recommend to store the products in sealed containers in a dry, cool place, and removed from volatile organic substances. Even if a product is stored under these conditions, after a longer period it can still pick up ambient moisture over time, which could lead to its exceeding the specified moisture content. For this reason, our recommended use-by date is 24 months after date of manufacture. Product more than 24 months old should be tested for moisture content before use in order to make certain that it is still suitable for the intended application.

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

Applied Technology

Evonik Resource Efficiency GmbH

Business Line Silica
Rodenbacher Chaussee 4
63457 Hanau-Wolfgang
Germany
PHONE +49 6181 59 3406
FAX +49 6181 59 4310
ask-si@evonik.com
www.acematt.com

Europe/ Middle-East/

Africa/ Latin America

Evonik Resource Efficiency GmbH

Business Line Silica
Rodenbacher Chaussee 4
63457 Hanau-Wolfgang
Germany
PHONE +49 6181 59 8118
FAX +49 6181 59 78118
ask-si@evonik.com
www.acematt.com

North America

Evonik Corporation

Business Line Silica
299 Jefferson Road
Parsippany, NJ 07054-0677
USA
PHONE +1 888 745-4227
FAX +1 732 981-5275
ask-si@evonik.com
www.acematt.com

Asia-Pacific

Evonik (SEA) Pte. Ltd.

Business Line Silica
3 International Business Park
#07-18, Nordic European Centre
Singapore 609927
PHONE +65 6 809 6851
FAX +65 6 809 6651
ask-si-asia@evonik.com
www.acematt.com