

# AERODISP® W 7520

## Aqueous dispersion of hydrophilic fumed silica

### Characteristic physico-chemical data

| Properties and test methods  | Unit | Value      |
|--|------|------------|
| pH value   |      | 9.5 - 10.5 |
| SiO <sub>2</sub> content   | %    | 19 - 21    |
| Stabilizing agent  |      | Ammonia    |
| Mean aggregate size d-50 value   | µm   | 0.12       |
| Viscosity measured at a shear rate of 100 s <sup>-1</sup>                    | mPas | ≤ 100      |
| * ex plant<br>The data represents typical values (no product specification). |      |            |

### Registrations (substance or product components)

#### AERODISP® W 7520

|  |  |
|--|--|
| CAS-No.*   | 112 945-52-5<br>(7631-86-9, old)   |
| EINECS (Europe),<br>TSCA (USA),<br>DSL (Canada),<br>AICS (Australia),<br>ENCS (Japan),<br>IECSC (China),<br>KECI (Korea) | All components of this dispersion are listed in the mentioned inventories. |

AERODISP® W 7520 is a low viscosity, water-based dispersion of AEROSIL® fumed silica, with a slightly alkaline pH.

### Applications and properties

#### Applications

- Rheology control
- Stabilization of emulsions
- Reinforcement
- Surface treatment, e.g. polishing
- Anti-blocking
- Anti-slip
- Adhesion promotion
- Flocculation aid

#### Properties

- Low thickening effect
- Low viscosity
- Slight ammonia odor

#### Appearance

- AERODISP® W 7520 is a milky-white liquid

### Safety and handling

Information concerning the safety of this product is listed in the corresponding Safety Data Sheet, which will be sent with the first delivery or upon updating. Such information is also available from Evonik Operations, Product Safety Department, E-MAIL [sds-im@evonik.com](mailto:sds-im@evonik.com) We recommend to read carefully the safety data sheet prior to the use of our product.

### Packaging and storage

Depending on the region, AERODISP® W 7520 is available in 60 kg containers, 220 kg drums and 1000 kg intermediate bulk containers (IBC's). All dispersions must be protected from extreme heat and frost. The product should be used within 18 months from the date of production. Small amounts of sedimentation are normal.

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

## Customer Service

**Europe/ Middle-East/  
Africa/ Latin America**  
**Evonik Operations GmbH**  
Business Line Silica  
PB 010-A410  
Rodenbacher Chaussee 4  
63457 Hanau-Wolfgang  
Germany  
PHONE +49 6181 59 12532  
FAX +49 6181 59 712532  
aerosil@evonik.com  
www.silica-specialist.com

**North America**  
**Evonik Corporation**  
Business Line Silica  
299 Jefferson Road  
Parsippany, NJ 07054-0677  
USA  
PHONE +1 800-233-8052  
FAX +1 973-929-8502  
aerosil@evonik.com  
www.silica-specialist.com

**Asia (excluding Japan)**  
**Evonik (SEA) Pte. Ltd.**  
Business Line Silica  
3 International Business Park  
Nordic European Centre, #07-18  
Singapore 609927  
PHONE +65 6809-6877  
FAX +65 6809-6677  
aerosil@evonik.com  
www.silica-specialist.com

**Japan**  
**NIPPON AEROSIL CO., LTD.**  
Marketing & Sales Division  
P.O. Box 7015  
Shinjuku Monolith 13F  
3-1, Nishi-Shinjuku 2-chrome  
Shinjuku-ku, Tokyo  
163-0913 Japan  
PHONE +81 3 3342-1789  
FAX +81 3 3342-1761  
infonac@evonik.com  
www.aerosil.jp

## Technical Service

**Europe/ Middle-East/  
Africa/ Latin America**  
**Evonik Operations**  
Business Line Silica  
HPC 911-221 A  
Rodenbacher Chaussee 4  
63457 Hanau-Wolfgang  
Germany  
PHONE +49 6181 59-3936  
FAX +49 6181 59 4489  
technical.service.aerosil@  
evonik.com  
www.silica-specialist.com

**North America**  
**Evonik Corporation**  
Business Line Silica  
2 Turner Place  
Piscataway, NJ 08855-0365  
USA  
PHONE +1 888 SILICAS  
PHONE +1 732 981-5000  
FAX +1 732 981-5275  
technical.service.aerosil@  
evonik.com  
www.silica-specialist.com

**Asia (excluding Japan)**  
**Evonik Specialty  
Chemicals (Shanghai) Co.,Ltd**  
Business Line Silica  
55 Chundong Road  
Xinzhuang Industry Park  
Shanghai 201108  
P.R. China  
PHONE +86 21 6119-1151  
FAX +86 21 6119-1075  
technical.service.aerosil@  
evonik.com  
www.silica-specialist.com

**Japan**  
**NIPPON AEROSIL CO., LTD.**  
Applied Technology Group  
3 Mita-Cho  
Yokkaichi, Mie  
510-0841 Japan  
PHONE +81 59 345-5270  
FAX +81 59 346-4657  
infonac@evonik.com  
www.aerosil.jp