

AEROSIL® OX 50

Hydrophilic fumed silica

Characteristic physico-chemical data

Properties and test methods	Unit	Value
Specific surface area (BET)	m ² /g	35 - 65
pH value in 4% Dispersion		3.8 - 4.8
Loss on drying* 2 hours at 105°C	%	≤ 1.5
Tamped density*	g/l	approx. 100
Sieve residue (by Mocker, 45µm)	%	≤ 0.200
SiO ₂ content based on ignited material	%	≥ 99.8
* ex plant The data represents typical values (no product specification)		

Registrations (substance or product components)

AEROSIL® OX 50

CAS-No.	112 945-52-5 (ex 7631-86-9)
REACH (Europe)	registered
TSCA (USA) DSL (Canada)	registered
ENCS (Japan) IECSC (China) KECI (Korea) CSNN (Taiwan) PICCS (Philippines)	registered
AICS (Australia) NZIoC (New Zealand)	registered

AEROSIL® OX 50 is a fumed silica with a very low specific surface area, low thickening, and high purity. The product can be used as an additive or as a raw material. In polymer composites, high filler loading can be achieved, making it possible to control essential characteristics of polymers.

Applications and properties

Properties

- Low thickening properties for high filler loading
- High tamped density
- Improvement in physicochemical characteristics of polymers, such as dielectric properties, optical properties, surface roughness, density, and hardness
- High purity

Applications

- Raw material for the production of ultra-pure glasses using the sol-gel process
- Additive in ceramics to control sintering activity or as raw material
- Filler in thermoplastic polymers and silicones
- Filler in composite materials
- Anti-blocking additive for polymer films with good transparency

Packaging and storage

AEROSIL® OX 50 is supplied in multiple layer 15 kg bags. We recommend to store the product in closed containers under dry conditions and to protect the material from volatile substances. AEROSIL® OX 50 should be used within 2 years after production.

Safety and handling

A safety data sheet will be provided with your first delivery and with subsequent revisions. Additionally, the Product Safety Department of Evonik Resource Efficiency GmbH can be contacted via mail at sds-hu@evonik.com for specific questions. We recommend to read the safety data sheet carefully prior to use of the product.

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

Customer Service

Europe/ Middle-East/ Africa/ Latin America

Evonik Resource Efficiency GmbH
Business Line Silica
PB 010-A410
Rodenbacher Chaussee 4
63457 Hanau-Wolfgang
Germany
PHONE +49 6181 59 12532
FAX +49 6181 59 712532
aerosil@evonik.com
www.aerosil.com

North America

Evonik Corporation
Business Line Silica
299 Jefferson Road
Parsippany, NJ 07054-0677
USA
PHONE +1 800-233-8052
FAX +1 973-929-8502
aerosil@evonik.com
www.aerosil.com

Asia (excluding Japan)

Evonik (SEA) Pte. Ltd.
Business Line Silica
3 International Business Park
Nordic European Centre, #07-18
Singapore 609927
PHONE +65 6809-6877
FAX +65 6809-6677
aerosil@evonik.com
www.aerosil.com

Japan

NIPPON AEROSIL CO., LTD.
Marketing & Sales Division
P.O. Box 7015
Shinjuku Monolith 13F
3-1, Nishi-Shinjuku 2-chrome
Shinjuku-ku, Tokyo
163-0913 Japan
PHONE +81 3 3342-1789
FAX +81 3 3342-1761
infonac@evonik.com
www.aerosil.jp

Technical Service

Europe/ Middle-East/ Africa/ Latin America

Evonik Resource Efficiency GmbH
Business Line Silica
HPC 911-221 A
Rodenbacher Chaussee 4
63457 Hanau-Wolfgang
Germany
PHONE +49 6181 59-3936
FAX +49 6181 59 4489
technical.service.aerosil@evonik.com
www.aerosil.com

North America

Evonik Corporation
Business Line Silica
2 Turner Place
Piscataway, NJ 08855-0365
USA
PHONE +1 888 SILICAS
PHONE +1 732 981-5000
FAX +1 732 981-5275
technical.service.aerosil@evonik.com
www.aerosil.com

Asia (excluding Japan)

**Evonik Specialty
Chemicals (Shanghai) Co.,Ltd**
Business Line Silica
55 Chundong Road
Xinzhuang Industry Park
Shanghai 201108
P.R. China
PHONE +86 21 6119-1151
FAX +86 21 6119-1075
technical.service.aerosil@evonik.com
www.aerosil.com

Japan

NIPPON AEROSIL CO., LTD.
Applied Technology Group
3 Mita-Cho
Yokkaichi, Mie
510-0841 Japan
PHONE +81 59 345-5270
FAX +81 59 346-4657
infonac@evonik.com
www.aerosil.jp