

AEROSIL® R 805 VV 90

Hydrophobic fumed silica

Characteristic physico-chemical data

Properties and test methods	Unit	Value
Specific surface area (BET)	m ² /g	125 - 175
pH value in 4% Dispersion		3.5 - 5.5
Loss on drying* 2 hours at 105 °C	%	≤ 0.5
C content	%	4.5 - 6.5
Tamped density*	g/l	approx. 90
SiO ₂ content based on ignited material	%	≥ 99.8

* ex plant

The data represents typical values (no product specification).

Registrations (substance or product components)

AEROSIL® R 805 VV 90

CAS-No.	92 797-60-9
REACH (Europe)	registered
TSCA (USA) DSL (Canada)	registered
ENCS (Japan) IECSC (China) KECI (Korea) CSNN (Taiwan) PICCS (Philippines)	registered
AICS (Australia) NZIoC (New Zealand)	registered

AEROSIL® R 805 VV 90 is a fumed silica aftertreated with organosilane.

Applications and properties

Properties

- Homogeneously hydrophobic surface
- Effective in the rheological control of complex liquid systems (such as paint and coating systems, adhesive and sealant materials)
- Efficient effect as flow agent
- Fine particle size

Applications

- Very efficient effect in thickening and thixotropy of complex polar liquids such as 2 K epoxy coatings
- Anti-settling agent and for pigment stabilization in coating applications
- The hydrophobia guarantees the efficient effect as flow agent in very different applications, such as powder coatings, toners, or cosmetics
- Rheology control for brilliant clear coat and top coats, such as acrylic/isocyanate coating formulations
- Enhances the anti-corrosion properties for coatings
- The hydrophobia makes the product suitable as an additive in anti-corrosion coatings

Safety and handling

A safety data sheet will be provided with your first delivery and with subsequent revisions. Additionally, the Product Safety Department of Evonik Resource Efficiency GmbH can be contacted via mail at sds-hu@evonik.com for specific questions. We recommend to read the safety data sheet carefully prior to use of the product.

Packaging and storage

AEROSIL® R 805 VV 90 is supplied in 90 kg Flexible Intermediate Bulk Containers (FIBC). We recommend to store the product in closed containers under dry conditions and to protect the material from volatile substances. AEROSIL® R 805 VV 90 should be used within 2 years after production.

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

Customer Service

Europe/ Middle-East/ Africa/ Latin America

Evonik Resource Efficiency GmbH

Business Line Silica
PB 010-A410
Rodenbacher Chaussee 4
63457 Hanau-Wolfgang
Germany
PHONE +49 6181 59 12532
FAX +49 6181 59 712532
aerosil@evonik.com
www.aerosil.com

North America

Evonik Corporation

Business Line Silica
299 Jefferson Road
Parsippany, NJ 07054-0677
USA
PHONE +1 800-233-8052
FAX +1 973-929-8502
aerosil@evonik.com
www.aerosil.com

Asia (excluding Japan)

Evonik (SEA) Pte. Ltd.

Business Line Silica
3 International Business Park
Nordic European Centre, #07-18
Singapore 609927
PHONE +65 6809-6877
FAX +65 6809-6677
aerosil@evonik.com
www.aerosil.com

Japan

NIPPON AEROSIL CO., LTD.

Marketing & Sales Division
P.O. Box 7015
Shinjuku Monolith 13F
3-1, Nishi-Shinjuku 2-chrome
Shinjuku-ku, Tokyo
163-0913 Japan
PHONE +81 3 3342-1789
FAX +81 3 3342-1761
infonac@evonik.com
www.aerosil.jp

Technical Service

Europe/ Middle-East/ Africa/ Latin America

Evonik Resource Efficiency GmbH

Business Line Silica
HPC 911-221 A
Rodenbacher Chaussee 4
63457 Hanau-Wolfgang
Germany
PHONE +49 6181 59-3936
FAX +49 6181 59 4489
technical.service.aerosil@evonik.com
www.aerosil.com

North America

Evonik Corporation

Business Line Silica
2 Turner Place
Piscataway, NJ 08855-0365
USA
PHONE +1 888 SILICAS
PHONE +1 732 981-5000
FAX +1 732 981-5275
technical.service.aerosil@evonik.com
www.aerosil.com

Asia (excluding Japan)

Evonik Specialty Chemicals (Shanghai) Co.,Ltd

Business Line Silica
55 Chundong Road
Xinzhuang Industry Park
Shanghai 201108
P.R. China
PHONE +86 21 6119-1151
FAX +86 21 6119-1075
technical.service.aerosil@evonik.com
www.aerosil.com

Japan

NIPPON AEROSIL CO., LTD.

Applied Technology Group
3 Mita-Cho
Yokkaichi, Mie
510-0841 Japan
PHONE +81 59 345-5270
FAX +81 59 346-4657
infonac@evonik.com
www.aerosil.jp