

# AEROXIDE® TiO<sub>2</sub> T 805

## Hydrophobic fumed titanium dioxide (TiO<sub>2</sub>)

### Characteristic physico-chemical data

Properties and test methods	Unit	Value
Specific surface area (BET)	m <sup>2</sup> /g	35 - 55
pH value in 4% dispersion		3.0 - 4.0
Loss on drying* 2 hours at 105°C	%	≤ 1.0
C content	%	2.7 - 3.7
Tamped density* modified	g/l	approx. 200
Fe <sub>2</sub> O <sub>3</sub> content based on ignited substance	%	≤ 0.010
TiO <sub>2</sub> content based on ignited substance	%	≥ 97.0
SiO <sub>2</sub> content based on ignited substance	%	≤ 2.500
* ex plant The data represents typical values (no product specification)		

### Registrations (substance or product components)

#### AEROXIDE® TiO<sub>2</sub> T 805

CAS-No.	100209-12-9 (ex 13463-67-7)
REACH (Europe)	registered
TSCA (USA) DSL (Canada)	registered
ENCS (Japan) IECSC (China) KECI (Korea) CSNN (Taiwan) PICCS (Philippines)	registered
AICS (Australia)	registered

AEROXIDE® TiO<sub>2</sub> T 805 is a fine-particulate, fumed titanium dioxide (TiO<sub>2</sub>) that is highly hydrophobized with an organosilane.

### Applications and properties

#### Properties

- High UV-B absorption
- High photostability
- Easy to disperse, especially in nonpolar liquids and fine-particulate solids

#### Applications

- Improves the flowability and stabilizes the electrostatic charging of toner powders for copiers and laser printers
- In polymer systems, the product can be used to increase the index of refraction

## Packaging and storage

AEROXIDE® TiO<sub>2</sub> T 805 is supplied in multiple layer 20 kg bags. We recommend to store the product in closed containers under dry conditions and to protect the material from volatile substances. AEROXIDE® TiO<sub>2</sub> T 805 should be used within 2 years after production.

## Safety and handling

A safety data sheet will be provided with your first delivery and with subsequent revisions. Additionally, the Product Safety Department of Evonik Resource Efficiency GmbH can be contacted via mail at [sds-hu@evonik.com](mailto:sds-hu@evonik.com) for specific questions. We recommend to read the safety data sheet carefully prior to use of the product.

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

### Customer Service

#### Europe/ Middle-East/ Africa/ Latin America

**Evonik Resource Efficiency GmbH**  
Business Line Silica  
PB 010-A410  
Rodenbacher Chaussee 4  
63457 Hanau-Wolfgang  
Germany  
PHONE +49 6181 59 12532  
FAX +49 6181 59 712532  
[aerosil@evonik.com](mailto:aerosil@evonik.com)  
[www.aerosil.com](http://www.aerosil.com)

#### North America

**Evonik Corporation**  
Business Line Silica  
299 Jefferson Road  
Parsippany, NJ 07054-0677  
USA  
PHONE +1 800-233-8052  
FAX +1 973-929-8502  
[aerosil@evonik.com](mailto:aerosil@evonik.com)  
[www.aerosil.com](http://www.aerosil.com)

#### Asia (excluding Japan)

**Evonik (SEA) Pte. Ltd.**  
Business Line Silica  
3 International Business Park  
Nordic European Centre, #07-18  
Singapore 609927  
PHONE +65 6809-6877  
FAX +65 6809-6677  
[aerosil@evonik.com](mailto:aerosil@evonik.com)  
[www.aerosil.com](http://www.aerosil.com)

#### Japan

**NIPPON AEROSIL CO., LTD.**  
Marketing & Sales Division  
P.O. Box 7015  
Shinjuku Monolith 13F  
3-1, Nishi-Shinjuku 2-chrome  
Shinjuku-ku, Tokyo  
163-0913 Japan  
PHONE +81 3 3342-1789  
FAX +81 3 3342-1761  
[infonac@evonik.com](mailto:infonac@evonik.com)  
[www.aerosil.jp](http://www.aerosil.jp)

### Technical Service

#### Europe/ Middle-East/ Africa/ Latin America

**Evonik Resource Efficiency GmbH**  
Business Line Silica  
HPC 911-221 A  
Rodenbacher Chaussee 4  
63457 Hanau-Wolfgang  
Germany  
PHONE +49 6181 59-3936  
FAX +49 6181 59 4489  
[technical.service.aerosil@evonik.com](mailto:technical.service.aerosil@evonik.com)  
[www.aerosil.com](http://www.aerosil.com)

#### North America

**Evonik Corporation**  
Business Line Silica  
2 Turner Place  
Piscataway, NJ 08855-0365  
USA  
PHONE +1 888 SILICAS  
PHONE +1 732 981-5000  
FAX +1 732 981-5275  
[technical.service.aerosil@evonik.com](mailto:technical.service.aerosil@evonik.com)  
[www.aerosil.com](http://www.aerosil.com)

#### Asia (excluding Japan)

**Evonik Specialty  
Chemicals (Shanghai) Co.,Ltd**  
Business Line Silica  
55 Chundong Road  
Xinzhuang Industry Park  
Shanghai 201108  
P.R. China  
PHONE +86 21 6119-1151  
FAX +86 21 6119-1075  
[technical.service.aerosil@evonik.com](mailto:technical.service.aerosil@evonik.com)  
[www.aerosil.com](http://www.aerosil.com)

#### Japan

**NIPPON AEROSIL CO., LTD.**  
Applied Technology Group  
3 Mita-Cho  
Yokkaichi, Mie  
510-0841 Japan  
PHONE +81 59 345-5270  
FAX +81 59 346-4657  
[infonac@evonik.com](mailto:infonac@evonik.com)  
[www.aerosil.jp](http://www.aerosil.jp)