

Dynasylan® 1189

N-(n-Butyl)-3-aminopropyltrimethoxysilane

Technical data

| Properties and test methods | Value | Unit | Method |
|-----------------------------|-------|-------------------|-----------|
| Density (20 °C) | 0.947 | g/cm ³ | DIN 51757 |
| Boiling point (1013 hPa) | 238 | °C | DIN 51751 |
| Viscosity (20 °C) | 2.5 | mPa.s | DIN 53015 |

Registrations

Dynasylan® 1189

| | |
|--------------------------|------------|
| EINECS/ELINCS (EU): | Yes |
| AICS (Australia): | No |
| DSL/NDSL (Canada): | * |
| PICCS (Philippines): | No |
| TSCA (USA): | Yes |
| IECS (P.R. China): | Yes |
| ENCS (Japan): | * |
| ECL (South Korea): | Yes |
| REACH (Europe) | Registered |
| * = available on request | |

Dynasylan® 1189 is a bifunctional silane possessing a reactive secondary amine and hydrolyzable methoxysilyl groups.

The dual nature of its reactivity allows Dynasylan® 1189 to bind chemically to both inorganic materials (e.g. glass, metals, fillers) and organic polymers (e.g. thermosets, thermoplastics and elastomers) thus functioning as an adhesion promoter or as a surface modifier and can be used for the chemical modification of substances.

Dynasylan® 1189 is a colorless to slight yellowish liquid with a light amine-like odor which is, for example, soluble in alcohols, and aliphatic or aromatic hydrocarbons.

Safety and handling

Before considering the use of Dynasylan® products please read its Safety Data sheet (SDS) thoroughly for safety and toxicological data as well as for information on proper transportation, storage and use. The Safety Data Sheet is available after registration on our website www.dynasylan.com or upon request from your local representative, customer service or from Evonik Resource Efficiency GmbH, Product Safety Department, E-MAIL sds-hu@evonik.com.

Packaging, storage and shelf life

Dynasylan® 1189 is supplied in 25 kg pails, 190 kg drums and 800 kg containers.

In the unopened container Dynasylan® 1189 has a shelf life of min. 12 months from delivery.

Properties and applications

Dynasylan® 1189 has many important applications.

Examples include:

- as a size constituent or finish for glass fiber/glass fabric composites
- as an additive to phenolic, furan and melamine resins used in foundry resins
- as a primer or additive and for the chemical modification of adhesives and sealants
- for pretreatment of fillers and pigments used in mineral-filled polymers
- as a primer and additive for improving the adhesion of paints and coatings to the substrate
- as a high flexible adhesion promoter in SMP-systems.

The most important product effects that can be achieved using Dynasylan® 1189 include:

- flexural strength, tensile strength, impact strength and modulus of elasticity
- improved moisture and corrosion resistance

Dynasylan® 1189 can also provide improvements in processing properties, such as

- adhesion
- filler dispersion
- rheological behavior: reduction in viscosity
- higher filler loading

Reactivity

In the presence of water, the methoxy groups of Dynasylan® 1189 hydrolyze to form reactive silanol groups which can bond to a variety of inorganic substrates. The organophilic n-butylamino group of Dynasylan® 1189 can react with a suitable polymer.

The hydrolysis of Dynasylan® 1189 in water takes place by acid catalysis (e.g. acetic acid at a pH of 3). To achieve solubility in organic solvents 2-4 wt.-% of water per wt.-% of Dynasylan® 1189 should be added. After stirring for 5 hours the solutions are ready for use.

Examples of suitable inorganic substrates are glass, glass fibres, glass wool, wollastonite and kaolin.

Dynasylan® 1189 may be used with such polymers as epoxy, polyurethanes, PA, PBT, EVA, modified PP and silicones.

In particular, Dynasylan® 1189 is a very effective coupling agent for thermoplastics. Superior mechanical properties can be achieved in reinforced MAA-modified PE or polypropylene matrices as well as polyamide. Dynasylan® 1189 especially leads to improvement of the impact strength of polyamide. Dynasylan® 1189 treated fibers and fillers deliver superior performance over standard aminosilanes in challenging environments. Dynasylan® 1189 can be used as an endcapper for polyurethanes (isocyanatoprepolymer).

Processing

For substrate pretreatments (inorganic fibers and fillers) Dynasylan® 1189 can be applied as a primer as a constituent of an aqueous size or solution, neat or added to the polymer as an additive. For substrate pretreatment a concentration of approx. 0.5-2 percent is recommended. Higher concentrations (1-5 wt.-%) achieve chemical modification by reaction with suitable functional monomers or polymers, for example those containing isocyanate groups.

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

Europe/Middle-East/Africa/RoW

Evonik Resource Efficiency GmbH

Business Line Silanes
Rodenbacher Chaussee 4
63457 Hanau-Wolfgang
Germany
PHONE +49 6181 59 13636
FAX +49 6181 59 713915
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific

Evonik (SEA) Pte. Ltd.

Business Line Silanes
3 Internatioanl Business Park
#07-18, Nordic European Centre
Singapore 609927
PHONE +65 6809 6576
FAX +65 6809 6699
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific

Evonik Japan Co. Ltd

Business Line Silanes
12th Floor Monolith Building
2-3-1, Nishi-Shinjuku-ku
Tokyo 163-0912
Japan
PHONE +81 353 23 7446
FAX +81 353 23 7397
dynasytan@evonik.com
www.dynasytan.com

North America

Evonik Corporation

Business Line Silanes
299 Jefferson Road
Parsippany, NJ 07054-0677
USA
PHONE (TOLL FREE) +1 800 237 67 45
PHONE +1 973 929 8513
FAX +1 973 929 8503
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific

**Evonik Specialty
Chemicals (Shanghai) Co. Ltd.**

Business Line Silanes
55, Chungdong Road
Xinzhuang Industry Park
Shanghai 201108
P.R. China
PHONE +86 21 61191-399
FAX +86 21 61191-648
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific

Evonik India Pvt. Ltd.

Business Line Silanes
Krislon House
Saki Vihar Road, Anderi (E)
Mumbai - 400 072
India
PHONE +91 226 7238 809
FAX +91 226 7238 811
dynasytan@evonik.com
www.dynasytan.com

North America

Silbond Corporation

9901 Sand Creek Highway
Weston, MI 49289
USA
PHONE +1 517 436 9316
FAX +1 517 436 3148
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific

Evonik Korea Ltd.

Business Line Silanes
94, Galsan 1-dong
Bupyeong-gu
Incheon, 403-081
Korea
PHONE +82 2320 4773
FAX +82 2783 2520
dynasytan@evonik.com
www.dynasytan.com

Latin America

Evonik Brasil Ltda.

Business Line Silanes
Alameda Campinas, 579
01404-000 São Paulo-SP
Brazil
PHONE +55 11 3146 4123
FAX +55 11 3146 4148
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific

Evonik Taiwan Ltd.

Business Line Silanes
Artist Construction Bldg.
9F, No. 133
Min Sheng East Road, Sec 3
Taipei, 105 Taiwan, R.O.C.
Taiwan 10596
PHONE +886 227 17 1242
FAX +886 227 17 2106
dynasytan@evonik.com
www.dynasytan.com