

Dynasytan® 2201 EQ

3-Ureidopropyltriethoxysilane, 50% solution in methanol, ethylcarbamate-free, contains no carcinogenic by-products

Technical data

| Properties and test methods | Value | Unit | Method |
|-----------------------------|------------------|-------------------|-----------|
| Density (20 °C/ 68 °F) | approx. 0.92 | g/cm ³ | DIN 51757 |
| Refractive index n(20,D) | approx. 1.39 | - | DIN 51423 |
| Viscosity (20 °C/ 68 °F) | approx. 2.5/ 2.7 | mPa's / cSt | DIN 53015 |
| Flash point | approx. 13/ 55 | °C/ °F | DIN 51755 |

Registrations

Dynasytan® 2201 EQ

| | |
|----------------------|-----|
| DSL/NDSL (Canada): | Yes |
| PICCS (Philippines): | Yes |
| TSCA (USA): | Yes |
| IECSC (P.R. China): | Yes |
| ENCS (Japan): | Yes |
| EINECS/ELINCS (EU): | Yes |
| AICS (Australia): | Yes |
| ECL (South Korea): | Yes |

Dynasytan® 2201 EQ is a bifunctional organosilane possessing a reactive organic ureido group and a hydrolyzable inorganic triethoxysilyl group.

The dual nature of its reactivity allows Dynasytan® 2201 EQ to bind chemically to both inorganic materials (e.g. glass, metals, fillers) and organic polymers (e.g. thermosets, thermoplastics, elastomers), thus functioning as an adhesion promoter and as a surface modifier. Dynasytan® 2201 EQ is a 50% solution of silane in methanol, is a colorless liquid with an alcohol-like odor and is soluble in alcohols, ketones, esters or aromatic hydrocarbons.

Due to novel patented process, Dynasytan® 2201 EQ is the first ureidofunctional silane, which contains no carcinogenic by-products, e.g. ethylcarbamate. Dynasytan® 2201 EQ is therefore **not** classified as "carcinogenic, class 2".

Safety and handling

Before considering the use of Dynasytan® products please read its Safety Data sheet (SDS) thoroughly for safety and toxicological data as well as for information on proper transportation, storage and use. The Safety Data Sheet is available after registration on our website www.dynasytan.com or upon request from your local representative, customer service or from Evonik Resource Efficiency GmbH, Product Safety Department, E-MAIL sds-hu@evonik.com.

Packaging, storage and shelf life

Dynasytan® 2201 EQ is supplied in 25 kg and 180 kg drums.

Dynasytan® 2201 EQ should be stored in a cool, well-ventilated place protected from moisture.

In the unopened container Dynasytan® 2201 EQ has a shelf life of at least 12 months from delivery.

Properties and applications

Dynasylan® 2201 EQ finds application in the products of many industries.

Examples are:

- as a size constituent of finish for glass fiber/glass fabric composites
- as an additive to phenolic, furan and melamine resins for foundry resins and abrasives
- as an additive for sealants and adhesives
- as an additive and/or primer for paints and varnishes to improve adhesion to the substrate

Important product effects that can be achieved through the use of Dynasylan® 2201 EQ are:

- improved mechanical properties: e.g. flexural strength, tensile strength, impact strength, modulus of elasticity
- improved resistance to moisture and corrosion
- higher temperature of deflection under load

Dynasylan® 2201 EQ also helps improve processing properties such as

- increased filler content

Reactivity

In the presence of water, the ethoxy (Si-OC₂H₅) groups of Dynasylan® 2201 EQ hydrolyze to form reactive silanol (Si-OH) groups which can bond to a variety of inorganic substrates. The organophilic ureido group of Dynasylan® 2201 EQ can react with a suitable polymer. Hydrolysis of Dynasylan® 2201 EQ can be catalyzed by acids.

Examples of suitable inorganic substrates are glass, glass fibers, glass wool.

Dynasylan® 2201 EQ may be used with such polymers as epoxy, phenolic, furan and melamine resins, polyurethanes, PA, PBT, PE, EVA, PP, PVB, PVAC, acrylics and silicones.

Processing

Dynasylan® 2201 EQ can be used for as a primer (approx. 1-10 wt.% solution in an organic solvent such as alcohol), or as a constituent of an aqueous size or solution.

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

Europe/Middle-East/Africa/RoW
Evonik Resource Efficiency GmbH

Business Line Silanes
Rodenbacher Chaussee 4
63457 Hanau-Wolfgang
Germany
PHONE +49 6181 59 13636
FAX +49 6181 59 713915
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific

Evonik (SEA) Pte. Ltd.

Business Line Silanes
3 Internatioanl Business Park
#07-18, Nordic European Centre
Singapore 609927
PHONE +65 6809 6576
FAX +65 6809 6699
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific

Evonik Japan Co. Ltd

Business Line Silanes
12th Floor Monolith Building
2-3-1, Nishi-Shinjuku-ku
Tokyo 163-0912
Japan
PHONE +81 353 23 7446
FAX +81 353 23 7397
dynasytan@evonik.com
www.dynasytan.com

North America

Evonik Corporation

Business Line Silanes
299 Jefferson Road
Parsippany, NJ 07054-0677
USA
PHONE (TOLL FREE) +1 800 237 67 45
PHONE +1 973 929 8513
FAX +1 973 929 8503
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific

Evonik Specialty

Chemicals (Shanghai) Co. Ltd.

Business Line Silanes
55, Chungdong Road
Xinzhuang Industry Park
Shanghai 201108
P.R. China
PHONE +86 21 61191-399
FAX +86 21 61191-648
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific

Evonik India Pvt. Ltd.

Business Line Silanes
Krislon House
Saki Vihar Road, Anderi (E)
Mumbai - 400 072
India
PHONE +91 226 7238 809
FAX +91 226 7238 811
dynasytan@evonik.com
www.dynasytan.com

North America

Silbond Corporation

9901 Sand Creek Highway
Weston, MI 49289
USA
PHONE +1 517 436 9316
FAX +1 517 436 3148
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific

Evonik Korea Ltd.

Business Line Silanes
94, Galsan 1-dong
Bupyeong-gu
Incheon, 403-081
Korea
PHONE +82 2320 4773
FAX +82 2783 2520
dynasytan@evonik.com
www.dynasytan.com

Latin America

Evonik Brasil Ltda.

Business Line Silanes
Alameda Campinas, 579
01404-000 São Paulo-SP
Brazil
PHONE +55 11 3146 4123
FAX +55 11 3146 4148
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific

Evonik Taiwan Ltd.

Business Line Silanes
Artist Construction Bldg.
9F, No. 133
Min Sheng East Road, Sec 3
Taipei, 105 Taiwan, R.O.C.
Taiwan 10596
PHONE +886 227 17 1242
FAX +886 227 17 2106
dynasytan@evonik.com
www.dynasytan.com