

Dynasytan® 4148

Polyethyleneglycol-functional alkoxy silane

Technical data

Properties and test methods	Value	Unit	Method
Viscosity (20 °C)	10 - 20	mPa.s	DIN 53015
Freezing point	< - 10	°C	DIN ISO 3016
Density (20 °C)	approx. 1.1	g/cm ³	DIN 51757
Flash point	> 95	°C	EN 22719

Registrations

Dynasytan® 4148

AICS (Australia):	No
DSL/NDL (Canada):	Yes
PICCS (Philippines):	No
TSCA (USA):	Yes
IECSC (P.R. China):	Yes
ENCS (Japan):	Yes
ECL (South Korea):	Yes
EINECS/ELINCS (EU):	Yes
REACH (Europe)	Exempted

Dynasytan® 4148 is a ready-for-use silane and is soluble in water and most organic solvents.

Dynasytan® 4148 helps to control rheological properties and to reduce viscosity in highly-filled polymer systems, like aluminum trihydroxide-filled polyesters or SMC-pastes.

Contrary to most other organofunctional silanes, Dynasytan® 4148 features chemical polarity yet remaining chemically not reactive. Such a product is used as a hydrophilic compatibilizer rather than a covalent adhesion promoter.

Dynasytan® 4148 permits workable viscosities at well over 250 phr aluminum trihydroxide loading in unsaturated polyester resins. Further more, Dynasytan® 4148 can be used as anti-settling agent for corrosion inhibitors in glycol based cooling agents.

As a non-coupling silane Dynasytan® 4148 can also be used as a slipping agent to simply modify a surface.

Safety and handling

Before considering the use of Dynasytan® products please read its Safety Data sheet (SDS) thoroughly for safety and toxicological data as well as for information on proper transportation, storage and use. The Safety Data Sheet is available after registration on our website www.dynasytan.com or upon request from your local representative, customer service or from Evonik Resource Efficiency GmbH, Product Safety Department, E-MAIL sds-hu@evonik.com.

Packaging, storage and shelf life

Dynasytan® 4148 is supplied in pails with a capacity of 25 kg and drums with 200 kg.

The containers must remain tightly sealed during storage and kept in a well aired place. Protection against humidity is essential.

Protect from frost (avoid temperatures below 0°C). The product becomes a solid when stored cold (e.g. at -10°C) but can be recovered without deterioration after melting.

In the unopened container Dynasytan® 4148 has a shelf life of min. 12 months from delivery.

Properties and applications

Dynasylan® 4148 can be added neatly to a blend of filler or pigment and resin, or it can be used for the pretreatment of the filler or pigment.

Pre-treatment of the filler or pigment is best achieved in a high-speed mixer by spraying Dynasylan® 4148 into a well-agitated filler or pigment bed. In order to obtain maximum efficiency of the treated filler or pigment, a good distribution of Dynasylan® 4148 throughout the filler or pigment surface is essential.

If the surface area of a filler or pigment is unknown, 1 percent by weight of Dynasylan® 4148, based on filler or pigment, is a convenient initial basis for Pre-treatment. Subsequently, the exact Dynasylan® 4148 loading should be determined empirically.

Moreover, Dynasylan® 4148 can act as a lubricant and wetting agent in the glass fibre industry in combination with silane coupling agents.

As a non-coupling silane, Dynasylan® 4148 can dramatically reduce the dispersion viscosity of aluminum trihydroxide and many other fillers and pigments. Because of better wetting and dispersion, outstanding filler or pigment loadings at a given viscosity can be realized with Dynasylan® 4148.

Dynasylan® 4148 helps to increase pigment dispersion predominantly in aqueous media, thus leading to an enhanced gloss of a typical coating.

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

Europe/Middle-East/Africa/RoW
Evonik Resource Efficiency GmbH

Business Line Silanes
Rodenbacher Chaussee 4
63457 Hanau-Wolfgang
Germany
PHONE +49 6181 59 13636
FAX +49 6181 59 713915
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific

Evonik (SEA) Pte. Ltd.

Business Line Silanes
3 Internatioanl Business Park
#07-18, Nordic European Centre
Singapore 609927
PHONE +65 6809 6576
FAX +65 6809 6699
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific

Evonik Japan Co. Ltd

Business Line Silanes
12th Floor Monolith Building
2-3-1, Nishi-Shinjuku-ku
Tokyo 163-0912
Japan
PHONE +81 353 23 7446
FAX +81 353 23 7397
dynasytan@evonik.com
www.dynasytan.com

North America

Evonik Corporation

Business Line Silanes
299 Jefferson Road
Parsippany, NJ 07054-0677
USA
PHONE (TOLL FREE) +1 800 237 67 45
PHONE +1 973 929 8513
FAX +1 973 929 8503
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific

Evonik Specialty

Chemicals (Shanghai) Co. Ltd.

Business Line Silanes
55, Chungdong Road
Xinzhuang Industry Park
Shanghai 201108
P.R. China
PHONE +86 21 61191-399
FAX +86 21 61191-648
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific

Evonik India Pvt. Ltd.

Business Line Silanes
Krislon House
Saki Vihar Road, Anderi (E)
Mumbai - 400 072
India
PHONE +91 226 7238 809
FAX +91 226 7238 811
dynasytan@evonik.com
www.dynasytan.com

North America

Silbond Corporation

9901 Sand Creek Highway
Weston, MI 49289
USA
PHONE +1 517 436 9316
FAX +1 517 436 3148
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific

Evonik Korea Ltd.

Business Line Silanes
94, Galsan 1-dong
Bupyeong-gu
Incheon, 403-081
Korea
PHONE +82 2320 4773
FAX +82 2783 2520
dynasytan@evonik.com
www.dynasytan.com

Latin America

Evonik Brasil Ltda.

Business Line Silanes
Alameda Campinas, 579
01404-000 São Paulo-SP
Brazil
PHONE +55 11 3146 4123
FAX +55 11 3146 4148
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific

Evonik Taiwan Ltd.

Business Line Silanes
Artist Construction Bldg.
9F, No. 133
Min Sheng East Road, Sec 3
Taipei, 105 Taiwan, R.O.C.
Taiwan 10596
PHONE +886 227 17 1242
FAX +886 227 17 2106
dynasytan@evonik.com
www.dynasytan.com