

# Dynasytan® 9116

## Hexadecyltrimethoxysilane

### Technical data

Properties and test methods	Value	Unit	Method
Flash point	165/ 329	°C/ °F	DIN 51758
Density (20 °C/ 68 °F)	0.89	g/cm <sup>3</sup>	DIN 51757
Viscosity, dynamic (20°C/ 68°F)	7	mPa·s (cSt)	DIN 53015
Boiling point (100 hPa)	180/ 356	°C/ °F	DIN 51751

### Registrations

#### Dynasytan® 9116

EINECS/ELINCS (EU):	Yes
AICS (Australia):	Yes
DSL/NDSL (Canada):	*
PICCS (Philippines):	Yes
TSCA (USA):	Yes
IECS (P.R. China):	Yes
ENCS (Japan):	Yes
ECL (South Korea):	Yes
REACH (Europe)	Registered
* = information on request	

Dynasytan® 9116 is a monomeric long-chain alkylfunctional silane.

Dynasytan® 9116 is a clear colourless liquid and soluble in common non-polar organic solvents (e.g. petroleum ether, toluene). However its low volatility and viscosity make Dynasytan® 9116 an easy-to-handle additive. During the hydrolysis reaction between water and Dynasytan® 9116 a certain amount of methanol (VOC) is released.

### Safety and handling

Before considering the use of Dynasytan® products please read its Safety Data sheet (SDS) thoroughly for safety and toxicological data as well as for information on proper transportation, storage and use. The Safety Data Sheet is available after registration on our website [www.dynasytan.com](http://www.dynasytan.com) or upon request from your local representative, customer service or from Evonik Resource Efficiency GmbH, Product Safety Department, E-MAIL [sds-hu@evonik.com](mailto:sds-hu@evonik.com).

### Packaging, storage and shelf life

Dynasytan® 9116 is supplied in 180 kg drums and 850 kg containers.

The containers must remain tightly sealed and stored in a cool, well-ventilated place protected against moisture.

Protect from frost (avoid temperatures below 0°C). The product becomes a solid when stored cold (e.g. at -10°C) but can be recovered without deterioration after melting.

In the unopened container Dynasytan® 9116 has a shelf life of min. 12 months from delivery.

## Properties and applications

Dynasylan® 9116 silane can be used for the treatment of mineral fillers and pigments or inorganic surfaces in general (e.g. concrete, ATH, MDH). The long-chain alkyl functionality results in unique compound properties (better dispersion, high filler loadings, enhanced mechanical properties, reduced water uptake) when Dynasylan® 9116 treated fillers are incorporated into polymers (e.g. polypropylene).

**Key Benefits:** Because of its unique structure, Dynasylan® 9116 exhibits superior hydrophobicity on substrates and forms weather- and moisture-resistant bonds to substrates as well. Use of Dynasylan® 9116 silane results in:

- waterproofing by impregnation when used as a water-repellent
- improvements in toughness in wollastonite-filled polypropylene, allowing the formulation of highly-filled compounds

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

**Europe/Middle-East/Africa/RoW**  
**Evonik Resource Efficiency GmbH**

Business Line Silanes  
Rodenbacher Chaussee 4  
63457 Hanau-Wolfgang  
Germany  
PHONE +49 6181 59 13636  
FAX +49 6181 59 713915  
dynasytan@evonik.com  
www.dynasytan.com

**Asia / Pacific**

**Evonik (SEA) Pte. Ltd.**

Business Line Silanes  
3 Internatioanl Business Park  
#07-18, Nordic European Centre  
Singapore 609927  
PHONE +65 6809 6576  
FAX +65 6809 6699  
dynasytan@evonik.com  
www.dynasytan.com

**Asia / Pacific**

**Evonik Japan Co. Ltd**

Business Line Silanes  
12th Floor Monolith Building  
2-3-1, Nishi-Shinjuku-ku  
Tokyo 163-0912  
Japan  
PHONE +81 353 23 7446  
FAX +81 353 23 7397  
dynasytan@evonik.com  
www.dynasytan.com

**North America**

**Evonik Corporation**

Business Line Silanes  
299 Jefferson Road  
Parsippany, NJ 07054-0677  
USA  
PHONE (TOLL FREE) +1 800 237 67 45  
PHONE +1 973 929 8513  
FAX +1 973 929 8503  
dynasytan@evonik.com  
www.dynasytan.com

**Asia / Pacific**

**Evonik Specialty**

**Chemicals (Shanghai) Co. Ltd.**

Business Line Silanes  
55, Chungdong Road  
Xinzhuang Industry Park  
Shanghai 201108  
P.R. China  
PHONE +86 21 61191-399  
FAX +86 21 61191-648  
dynasytan@evonik.com  
www.dynasytan.com

**Asia / Pacific**

**Evonik India Pvt. Ltd.**

Business Line Silanes  
Krislon House  
Saki Vihar Road, Anderi (E)  
Mumbai - 400 072  
India  
PHONE +91 226 7238 809  
FAX +91 226 7238 811  
dynasytan@evonik.com  
www.dynasytan.com

**North America**

**Silbond Corporation**

9901 Sand Creek Highway  
Weston, MI 49289  
USA  
PHONE +1 517 436 9316  
FAX +1 517 436 3148  
dynasytan@evonik.com  
www.dynasytan.com

**Asia / Pacific**

**Evonik Korea Ltd.**

Business Line Silanes  
94, Galsan 1-dong  
Bupyeong-gu  
Incheon, 403-081  
Korea  
PHONE +82 2320 4773  
FAX +82 2783 2520  
dynasytan@evonik.com  
www.dynasytan.com

**Latin America**

**Evonik Brasil Ltda.**

Business Line Silanes  
Alameda Campinas, 579  
01404-000 São Paulo-SP  
Brazil  
PHONE +55 11 3146 4123  
FAX +55 11 3146 4148  
dynasytan@evonik.com  
www.dynasytan.com

**Asia / Pacific**

**Evonik Taiwan Ltd.**

Business Line Silanes  
Artist Construction Bldg.  
9F, No. 133  
Min Sheng East Road, Sec 3  
Taipei, 105 Taiwan, R.O.C.  
Taiwan 10596  
PHONE +886 227 17 1242  
FAX +886 227 17 2106  
dynasytan@evonik.com  
www.dynasytan.com