

Dynasytan® AMMO

3-Aminopropyltrimethoxysilane

Technical data

Properties and test methods	Value	Unit	Method
Density (20 °C/ 68 °F)	approx. 1.02	g/cm ³	DIN 51757
Refractive index n(20,D)	approx. 1.425	-	DIN 51423
Viscosity (20 °C/ 68 °F)	approx. 2/1.95	mPa's / cSt	DIN 53015
Boiling point (1013 hPa/ 760 Torr)	194/ 381	°C/ °F	DIN 51751
Flash point	90/ 194	°C/ °F	EN 22719

Registrations

Dynasytan® AMMO

EINECS/ELINCS (EU):	Yes
AICS (Australia):	Yes
DSL/NDSL (Canada):	Yes
PICCS (Philippines):	Yes
TSCA (USA):	Yes
IECS (P.R. China):	Yes
ENCSC (Japan):	Yes
ECL (South Korea):	Yes
REACH (Europe)	Registered

Dynasytan® AMMO is a bifunctional organosilane possessing a reactive primary amine and hydrolyzable inorganic methoxysilyl groups.

The dual nature of its reactivity allows Dynasytan® AMMO to bind chemically to both inorganic materials (e.g. glass, metals fillers) and organic polymers (e.g. thermosets, thermoplastics and elastomers), thus functioning as an adhesion promoter and a surface modifier. Dynasytan® AMMO is a clear, colorless liquid having an amine-like odor which is soluble in alcohols and aliphatic and aromatic hydrocarbons.

Safety and handling

Before considering the use of Dynasytan® products please read its Safety Data sheet (SDS) thoroughly for safety and toxicological data as well as for information on proper transportation, storage and use. The Safety Data Sheet is available after registration on our website www.dynasytan.com or upon request from your local representative, customer service or from Evonik Resource Efficiency GmbH, Product Safety Department, E-MAIL sds-hu@evonik.com.

Packaging, storage and shelf life

Dynasytan® AMMO is supplied in 25, 200 kg drums and 1.000 kg IBC containers.

In the unopened container Dynasytan® AMMO has a shelf life of min. 12 months from delivery.

Properties and applications

Dynasylan® AMMO is an important additive in many applications.

Examples include:

- glass fiber/glass fabric composites: as a size ingredient or finish
- glass and metal primers
- foundry resins: as an additive to cold-curing phenolic and furan resins
- sealants and adhesives: as a primer or additive and for chemical modification
- mineral-filled composites: for pretreatment of fillers and pigments
- paints and coatings: as an additive and primer for improving adhesion to the substrate.

Important product effects which can be achieved using Dynasylan® AMMO are:

- improved mechanical properties, for example flexural strength, tensile strength, impact strength and modulus of elasticity
- improved moisture and corrosion resistance
- improved electrical properties, for example dielectric constant, volume resistivity

Dynasylan® AMMO can also improve processing properties such as

- adhesion
- filler dispersion
- rheological behavior: reduction in viscosity, Newtonian behavior
- increased filler loading

Reactivity

In the presence of water, the methoxy groups of Dynasylan® AMMO hydrolyze form reactive silanol groups which can bond to a variety of inorganic substrates. The organophilic amino group of Dynasylan® AMMO can react with a suitable polymer. Hydrolysis of Dynasylan® AMMO takes place autocatalytically. The pH of the hydrolysate is about 10-11.

Examples of suitable inorganic substrates are glass, glass fibers, glass wool, mineral wool, silicic acid, quartz, sand, cristobalite, wollastonite and mica as well as aluminum hydroxide, kaolin, talc, other silicate fillers, metal oxides and metals.

Dynasylan® AMMO may be used with such polymers as epoxy, phenolic, furan and melamine resins, polyurethanes, PA, PBT, PC, EVA, modified PP, PVB, PVAC, PVC, acrylics and silicones. Dynasylan® AMMO can undergo reactions with ketone or ester solvents. The silanes or silanized substrates can react with carbon dioxide to form the corresponding carbonates or carbamates, respectively. Product modifications are possible through addition reactions with suitable monomeric or polymeric compounds (for example isocyanates, epoxides).

Processing

Dynasylan® AMMO can be used as an approx. 0.5-10 wt.% solution in an organic solvent or as a constituent of an aqueous size. It may also be used neat or can be added to the polymer as an additive. Chemical modification can be achieved by reaction of Dynasylan® AMMO with suitable functional monomers or polymers, for example those containing isocyanate or epoxy groups.

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

Europe/Middle-East/Africa/RoW
Evonik Resource Efficiency GmbH

Business Line Silanes
Rodenbacher Chaussee 4
63457 Hanau-Wolfgang
Germany
PHONE +49 6181 59 13636
FAX +49 6181 59 713915
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific

Evonik (SEA) Pte. Ltd.

Business Line Silanes
3 Internatioanl Business Park
#07-18, Nordic European Centre
Singapore 609927
PHONE +65 6809 6576
FAX +65 6809 6699
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific

Evonik Japan Co. Ltd

Business Line Silanes
12th Floor Monolith Building
2-3-1, Nishi-Shinjuku-ku
Tokyo 163-0912
Japan
PHONE +81 353 23 7446
FAX +81 353 23 7397
dynasytan@evonik.com
www.dynasytan.com

North America

Evonik Corporation

Business Line Silanes
299 Jefferson Road
Parsippany, NJ 07054-0677
USA
PHONE (TOLL FREE) +1 800 237 67 45
PHONE +1 973 929 8513
FAX +1 973 929 8503
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific

Evonik Specialty

Chemicals (Shanghai) Co. Ltd.

Business Line Silanes
55, Chungdong Road
Xinzhuang Industry Park
Shanghai 201108
P.R. China
PHONE +86 21 61191-399
FAX +86 21 61191-648
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific

Evonik India Pvt. Ltd.

Business Line Silanes
Krislon House
Saki Vihar Road, Anderi (E)
Mumbai - 400 072
India
PHONE +91 226 7238 809
FAX +91 226 7238 811
dynasytan@evonik.com
www.dynasytan.com

North America

Silbond Corporation

9901 Sand Creek Highway
Weston, MI 49289
USA
PHONE +1 517 436 9316
FAX +1 517 436 3148
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific

Evonik Korea Ltd.

Business Line Silanes
94, Galsan 1-dong
Bupyeong-gu
Incheon, 403-081
Korea
PHONE +82 2320 4773
FAX +82 2783 2520
dynasytan@evonik.com
www.dynasytan.com

Latin America

Evonik Brasil Ltda.

Business Line Silanes
Alameda Campinas, 579
01404-000 São Paulo-SP
Brazil
PHONE +55 11 3146 4123
FAX +55 11 3146 4148
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific

Evonik Taiwan Ltd.

Business Line Silanes
Artist Construction Bldg.
9F, No. 133
Min Sheng East Road, Sec 3
Taipei, 105 Taiwan, R.O.C.
Taiwan 10596
PHONE +886 227 17 1242
FAX +886 227 17 2106
dynasytan@evonik.com
www.dynasytan.com