

Dynasylan® HYDROSIL 2926

Reactive organofunctional siloxane oligomer in water

Technical data

Properties and test methods	Value	Unit	Method
Density (20 °C)	1.091	g/cm ³	DIN 51757
Color	< 1	Gardner	ISO 4630
Flash point	> 98	°C	DIN 51755
Viscosity (20 °C)	6-7	mPa·s	DIN 53015
pH (20 °C, 1:1 in H ₂ O)	3	-	DIN 19268

Registrations

Dynasylan® HYDROSIL 2926

EINECS/ELINCS (EU):	Yes
AICS (Australia):	Yes
DSL/NDSL (Canada):	Yes
PICCS (Philippines):	Yes
TSCA (USA):	Yes
IECSC (P.R. China):	Yes
ENCS (Japan):	*
ECL (South Korea):	Yes
REACH (Europe)	Exempted
* available on request	

Dynasylan® HYDROSIL 2926 provides the producer of high-performance laminate materials with an adhesion promoter between inorganic materials (glass, minerals and metals) and organic polymers (thermosets, thermoplastics and elastomers).

Dynasylan® HYDROSIL 2926 is a colorless liquid.

Safety and handling

Before considering the use of Dynasylan® products please read its Safety Data Sheet (SDS) thoroughly for safety and toxicological data as well as for information on proper transportation, storage and use. The Safety Data Sheet is available after registration on our website www.dynasylan.com or upon request from your local representative, customer service or from Evonik Resource Efficiency GmbH, Product Safety Department, E-MAIL sds-hu@evonik.com.

Packaging, storage and shelf life

In the originally sealed containers Dynasylan® HYDROSIL 2926 has a shelf life of min. 12 months from delivery.

It is recommended to store Dynasylan® HYDROSIL 2926 above freezing temperatures.

Dynasylan® HYDROSIL 2926 is supplied in 25 kg, 200 kg drums and 1.000 kg bulk containers.

Properties and applications

Properties

Dynasylan® HYDROSIL 2926 is an organosilicon compound based on water as the solvent and contains no volatile organic constituents.

Applications

- Surface treatment of minerals
- Glass fibre reinforcement
- Priming of glass and metal
- Surface modifier for organic materials
- Additive for water-borne polymer systems

Depending on the area of application a concentration of active compound of approx. 0.5-5% may be employed. As a consequence, Dynasylan® HYDROSIL 2926 can be simply diluted with distilled water. A 5 wt.-% aqueous solution at pH 4-9 has a pot life of about 1 year.

The following advantages are obtained over solution conventional organofunctional silanes:

Increased product and processing reliability:

- no liberation of flammable organic constituents
- flash point > 98 °C

Process flexibility:

- processing possible at elevated temperatures and in the vicinity of ignition sources or static charge

Applicational advantage:

- in polymer systems based on water as the solvent

Environmental protection:

- hydrolysis does not result in liberation of volatile organic substances

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

Europe/Middle-East/Africa/RoW

Evonik Resource Efficiency GmbH

Business Line Silanes
Rodenbacher Chaussee 4
63457 Hanau-Wolfgang
Germany
PHONE +49 6181 59 13636
FAX +49 6181 59 713915
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific

Evonik (SEA) Pte. Ltd.

Business Line Silanes
3 Internatioanl Business Park
#07-18, Nordic European Centre
Singapore 609927
PHONE +65 6809 6576
FAX +65 6809 6699
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific

Evonik Japan Co. Ltd

Business Line Silanes
12th Floor Monolith Building
2-3-1, Nishi-Shinjuku-ku
Tokyo 163-0912
Japan
PHONE +81 353 23 7446
FAX +81 353 23 7397
dynasytan@evonik.com
www.dynasytan.com

North America

Evonik Corporation

Business Line Silanes
299 Jefferson Road
Parsippany, NJ 07054-0677
USA
PHONE (TOLL FREE) +1 800 237 67 45
PHONE +1 973 929 8513
FAX +1 973 929 8503
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific

**Evonik Specialty
Chemicals (Shanghai) Co. Ltd.**

Business Line Silanes
55, Chungdong Road
Xinzhuang Industry Park
Shanghai 201108
P.R. China
PHONE +86 21 61191-399
FAX +86 21 61191-648
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific

Evonik India Pvt. Ltd.

Business Line Silanes
Krislon House
Saki Vihar Road, Anderi (E)
Mumbai - 400 072
India
PHONE +91 226 7238 809
FAX +91 226 7238 811
dynasytan@evonik.com
www.dynasytan.com

North America

Silbond Corporation

9901 Sand Creek Highway
Weston, MI 49289
USA
PHONE +1 517 436 9316
FAX +1 517 436 3148
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific

Evonik Korea Ltd.

Business Line Silanes
94, Galsan 1-dong
Bupyeong-gu
Incheon, 403-081
Korea
PHONE +82 2320 4773
FAX +82 2783 2520
dynasytan@evonik.com
www.dynasytan.com

Latin America

Evonik Brasil Ltda.

Business Line Silanes
Alameda Campinas, 579
01404-000 São Paulo-SP
Brazil
PHONE +55 11 3146 4123
FAX +55 11 3146 4148
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific

Evonik Taiwan Ltd.

Business Line Silanes
Artist Construction Bldg.
9F, No. 133
Min Sheng East Road, Sec 3
Taipei, 105 Taiwan, R.O.C.
Taiwan 10596
PHONE +886 227 17 1242
FAX +886 227 17 2106
dynasytan@evonik.com
www.dynasytan.com