

# Dynasytan® SIVO 210

## Proprietary aminofunctional silane composition

### Technical data

Properties and test methods	Value	Unit	Method
Density (20 °C)	approx. 0.97	g/cm <sup>3</sup>	DIN 51757
pH value (20 °C / 1:1 in H <sub>2</sub> O)	approx. 11	-	-
Viscosity (20 °C)	approx. 4-40	mPa's	DIN 53015
Boiling point (1013 hPa)	240	°C	ASTM D-1120
Flash point	> 95	°C	DIN EN ISO 2719

### Registrations

#### Dynasytan® SIVO 210

EINECS/ELINCS (EU):	Yes
AICS (Australia):	No
DSL/NDSL (Canada):	No
PICCS (Philippines):	Yes
TSCA (USA):	Yes
IECSC (P.R. China):	Yes
ENCS (Japan):	*
ECL (South Korea):	Yes
* = information on request	

Dynasytan® SIVO 210 is an aminofunctional silane composition which acts as an adhesion promoter between inorganic materials (for example glass, metals and fillers) and organic polymers (thermosets, thermoplastics and elastomers), as a surface modifier or as chemical modification of substances.

Dynasytan® SIVO 210 is a colorless to yellowish liquid with an amine-like odor which is soluble in alcohols, aliphatic or aromatic hydrocarbons.

### Safety and handling

Before considering the use of Dynasytan® products please read its Safety Data Sheet (SDS) thoroughly for safety and toxicological data as well as for information on proper transportation, storage and use. The Safety Data Sheet is available after registration on our website [www.dynasytan.com](http://www.dynasytan.com) or upon request from your local representative, customer service or from Evonik Resource Efficiency GmbH, Product Safety Department, E-MAIL [sds-hu@evonik.com](mailto:sds-hu@evonik.com).

### Packaging, storage and shelf life

Dynasytan® SIVO 210 is supplied in 25 kg pails, 180 kg drums and 900 kg IBC containers.

In originally sealed containers Dynasytan® SIVO 210 has a shelf life of min. 12 months from delivery.

## Properties and applications

Dynasylan® SIVO 210 is an important additive in many applications.

### Examples are:

- metal primers
- foundry resins: as additive to phenolic, furan and melamine resins
- sealants and adhesives: as primer or additive
- mineral-filled polymers (composites) or HFFR cables: for pretreatment of fillers and pigments
- paints and coatings: as additive and primer for improving adhesion to the substrate.

The most important effects which can be achieved using Dynasylan® SIVO 210 are:

### improvement in product properties, such as:

- mechanical properties, for example flexural strength, tensile strength, impact strength and modulus of elasticity
- moisture and corrosion resistance

### improvement in processing properties, such as:

- adhesion
- filler dispersion
- rheological behaviour: reduction in viscosity, Newtonian behaviour
- higher filler loading

## Reactivity

Dynasylan® SIVO 210 contains primary and secondary aminoalkylethoxysilanes. The components are bifunctional organic compounds in which the silicon-functional ethoxy-groups hydrolyze in the presence of water to form reactive silanols, which can be bonded to an inorganic substrate; the organophilic amino group can interact with a suitable polymer. The composition contains partly six hydrolyzable substituents in one molecule. Thus Dynasylan® SIVO 210 is exceptionally suitable to form highly crosslinked networks on and between substrates and in organic matrices.

The hydrolysis of Dynasylan® SIVO 210 in water takes place by acidic catalysis (e.g. formic or acetic acid at a pH 3). To achieve solubility in organic solvents simply add 2-4 wt.-% of water per wt.-% of Dynasylan® SIVO 210. Upon stirring for 5h the solutions are ready for use.

Examples of suitable inorganic substrates are glass, silicic acid, quartz, sand, cristobalite, wollastonite and mica; also suitable are aluminium hydroxide, kaolin, talc, other silicate fillers, metal oxides and metals.

Examples of suitable polymers are phenolic resins, furane resins, melamine resins, PA, PBT, PC, EVA, modified PP, PVB, PVAC, PVC.

The secondary amino group in Dynasylan® SIVO 210 provides high basicity at somewhat lower reactivity compared to the primary amino groups. This is of major advantage in e.g. HFFR cables where the silane is added to the polymer matrix. Homogeneous distribution and bonding/networking of Dynasylan® SIVO 210 to the inorganic filler can commence unless bonding to organic materials (e.g. polymers) will proceed.

Excellent crosslinking properties make Dynasylan® SIVO 210 a preferred component in the silylation of inorganic filler surfaces and in corrosion-resistant primer systems for metal pretreatment.

## Processing

Dynasylan® SIVO 210 can advantageously be employed in organic solvents as constituent of aqueous sizes or solutions or added to the polymer as an additive. In higher concentrations (1-5 wt.-%) chemical modification can be achieved by reaction with suitable functional monomers or polymers, for example those containing epoxy groups.

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

**Europe/Middle-East/Africa/RoW**  
**Evonik Resource Efficiency GmbH**

Business Line Silanes  
Rodenbacher Chaussee 4  
63457 Hanau-Wolfgang  
Germany  
PHONE +49 6181 59 13636  
FAX +49 6181 59 713915  
dynasytan@evonik.com  
www.dynasytan.com

**Asia / Pacific**

**Evonik (SEA) Pte. Ltd.**

Business Line Silanes  
3 Internatioanl Business Park  
#07-18, Nordic European Centre  
Singapore 609927  
PHONE +65 6809 6576  
FAX +65 6809 6699  
dynasytan@evonik.com  
www.dynasytan.com

**Asia / Pacific**

**Evonik Japan Co. Ltd**

Business Line Silanes  
12th Floor Monolith Building  
2-3-1, Nishi-Shinjuku-ku  
Tokyo 163-0912  
Japan  
PHONE +81 353 23 7446  
FAX +81 353 23 7397  
dynasytan@evonik.com  
www.dynasytan.com

**North America**

**Evonik Corporation**

Business Line Silanes  
299 Jefferson Road  
Parsippany, NJ 07054-0677  
USA  
PHONE (TOLL FREE) +1 800 237 67 45  
PHONE +1 973 929 8513  
FAX +1 973 929 8503  
dynasytan@evonik.com  
www.dynasytan.com

**Asia / Pacific**

**Evonik Specialty**

**Chemicals (Shanghai) Co. Ltd.**

Business Line Silanes  
55, Chungdong Road  
Xinzhuang Industry Park  
Shanghai 201108  
P.R. China  
PHONE +86 21 61191-399  
FAX +86 21 61191-648  
dynasytan@evonik.com  
www.dynasytan.com

**Asia / Pacific**

**Evonik India Pvt. Ltd.**

Business Line Silanes  
Krislon House  
Saki Vihar Road, Anderi (E)  
Mumbai - 400 072  
India  
PHONE +91 226 7238 809  
FAX +91 226 7238 811  
dynasytan@evonik.com  
www.dynasytan.com

**North America**

**Silbond Corporation**

9901 Sand Creek Highway  
Weston, MI 49289  
USA  
PHONE +1 517 436 9316  
FAX +1 517 436 3148  
dynasytan@evonik.com  
www.dynasytan.com

**Asia / Pacific**

**Evonik Korea Ltd.**

Business Line Silanes  
94, Galsan 1-dong  
Bupyeong-gu  
Incheon, 403-081  
Korea  
PHONE +82 2320 4773  
FAX +82 2783 2520  
dynasytan@evonik.com  
www.dynasytan.com

**Latin America**

**Evonik Brasil Ltda.**

Business Line Silanes  
Alameda Campinas, 579  
01404-000 São Paulo-SP  
Brazil  
PHONE +55 11 3146 4123  
FAX +55 11 3146 4148  
dynasytan@evonik.com  
www.dynasytan.com

**Asia / Pacific**

**Evonik Taiwan Ltd.**

Business Line Silanes  
Artist Construction Bldg.  
9F, No. 133  
Min Sheng East Road, Sec 3  
Taipei, 105 Taiwan, R.O.C.  
Taiwan 10596  
PHONE +886 227 17 1242  
FAX +886 227 17 2106  
dynasytan@evonik.com  
www.dynasytan.com