

# Dynasytan® SILBOND® H-25

## Ethyl polysilicates

### Technical Data

| Properties and test methods           | Unit              | Value         |
|---------------------------------------|-------------------|---------------|
| Form                                  | -                 | Clear Liquid  |
| Density (20 °C)                       | g/cm <sup>3</sup> | 0.940 - 0.960 |
| Boiling Point                         | °C / °F           | 78 / 172      |
| Flash Point                           | °C / °F           | 13 / 56       |
| Silica content (as SiO <sub>2</sub> ) | % wt min          | 24.5          |

Dynasytan® SILBOND® H-25 is a clear, low-viscosity pre-hydrolyzed ethyl polysilicate binder with minimum 24.5% silica (as SiO<sub>2</sub>). Its primary use is in the production of facings and molds for precision investment casting. Other applications include formation of ceramic shapes and cores.

### Safety and handling

Before considering the use of Dynasytan® SILBOND® products please read its Safety Data Sheet (SDS) thoroughly for safety and toxicological data as well as for information on proper transportation, storage and use. The Safety Data Sheet is available after registration on our website [www.dynasytan.com](http://www.dynasytan.com) or upon request from your local representative, customer service or from Evonik Resource Efficiency GmbH, Product Safety Department, E-MAIL [sds-hu@evonik.com](mailto:sds-hu@evonik.com).

### Packaging, storage and shelf life

Dynasytan® SILBOND® H-25 could be available in pails, drums, totes, and tanker quantities.

In the unopened container Dynasytan® SILBOND® H-25 has a shelf life of min. 6 months from date of manufacture.

Please ask us for further details.

## Properties and applications

Dynasylan® SILBOND® H-25 can be used, as delivered, to make ceramic molds for the Precision Investment Casting industry.

The degree of hydrolysis and acidity have been optimized for the required reactivity and sufficient storage stability.

The hydrolysis and condensation has been started during the production of the binder. Through a shift in the pH this process is accelerated. This shift is achieved by addition of fillers, pigments, additive, or through the evaporation of solvent or exposure to atmospheric moisture. The resulting silicic acid gel cures rapidly at ambient temperatures in air. The process of curing can be accelerated through the addition of alkali catalysts.

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

### Europe/Middle-East/Africa/RoW Evonik Resource Efficiency GmbH

Business Line Silanes  
Rodenbacher Chaussee 4  
63457 Hanau-Wolfgang  
Germany  
PHONE +49 6181 59 13636  
FAX +49 6181 59 713915  
dynasylan@evonik.com  
www.dynasylan.com

### Asia / Pacific

#### Evonik (SEA) Pte. Ltd.

Business Line Silanes  
3 Internatioanl Business Park  
#07-18, Nordic European Centre  
Singapore 609927  
PHONE +65 6809 6576  
FAX +65 6809 6699  
dynasylan@evonik.com  
www.dynasylan.com

### Asia / Pacific

#### Evonik Japan Co. Ltd

Business Line Silanes  
12th Floor Monolith Building  
2-3-1, Nishi-Shinjuku-ku  
Tokyo 163-0912  
Japan  
PHONE +81 353 23 7446  
FAX +81 353 23 7397  
dynasylan@evonik.com  
www.dynasylan.com

### North America

#### Evonik Corporation

Business Line Silanes  
299 Jefferson Road  
Parsippany, NJ 07054-0677  
USA  
PHONE (TOLL FREE) +1 800 237 67 45  
PHONE +1 973 929 8513  
FAX +1 973 929 8503  
dynasylan@evonik.com  
www.dynasylan.com

### Asia / Pacific

#### Evonik Specialty

#### Chemicals (Shanghai) Co. Ltd.

Business Line Silanes  
55, Chungdong Road  
Xinzhuang Industry Park  
Shanghai 201108  
P.R. China  
PHONE +86 21 61191-399  
FAX +86 21 61191-648  
dynasylan@evonik.com  
www.dynasylan.com

### Asia / Pacific

#### Evonik India Pvt. Ltd.

Business Line Silanes  
Krislon House  
Saki Vihar Road, Anderi (E)  
Mumbai - 400 072  
India  
PHONE +91 226 7238 809  
FAX +91 226 7238 811  
dynasylan@evonik.com  
www.dynasylan.com

### North America

#### Silbond Corporation

9901 Sand Creek Highway  
Weston, MI 49289  
USA  
PHONE +1 517 436 9316  
FAX +1 517 436 3148  
dynasylan@evonik.com  
www.dynasylan.com

### Asia / Pacific

#### Evonik Korea Ltd.

Business Line Silanes  
94, Galsan 1-dong  
Bupyeong-gu  
Incheon, 403-081  
Korea  
PHONE +82 2320 4773  
FAX +82 2783 2520  
dynasylan@evonik.com  
www.dynasylan.com

### Latin America

#### Evonik Brasil Ltda.

Business Line Silanes  
Alameda Campinas, 579  
01404-000 São Paulo-SP  
Brazil  
PHONE +55 11 3146 4123  
FAX +55 11 3146 4148  
dynasylan@evonik.com  
www.dynasylan.com

### Asia / Pacific

#### Evonik Taiwan Ltd.

Business Line Silanes  
Artist Construction Bldg.  
9F, No. 133  
Min Sheng East Road, Sec 3  
Taipei, 105 Taiwan, R.O.C.  
Taiwan 10596  
PHONE +886 227 17 1242  
FAX +886 227 17 2106  
dynasylan@evonik.com  
www.dynasylan.com