

# Dynasytan® VTMOEO

## Vinyltris(2-methoxyethoxy)silane

### Technical data

Properties and test methods	Value	Unit	Method
Density (20 °C/ 68 °F)	approx. 1.040	g/cm <sup>3</sup>	DIN 51757
Refractive index n(20, D)	approx. 1.430	-	DIN 51423
Boiling point (1013 hPA)	approx. 258 / 545	°C/ °F	DIN 51751
Flash point	approx. 115/ 239	°C/ °F	DIN 51758
Viscosity (20 °C/ 68 °F)	approx. 2.7/ 2.6	mPa·s /cSt	DIN 53015

### Registrations

#### Dynasytan® VTMOEO

ECL (South Korea):	Yes
EINECS/ELINCS (EU):	Yes
AICS (Australia):	Yes
DSL/NDL (Canada):	Yes
PICCS (Philippines):	Yes
TSCA (USA):	Yes
IECS (P.R. China):	Yes
ENCS (Japan):	Yes
REACH (Europe)	Registered

Dynasytan® VTMOEO is a bifunctional organosilane possessing a reactive vinyl group and a hydrolyzable 2-methoxy-ethoxy-silyl group.

The dual nature of its reactivity allows Dynasytan® VTMOEO to bind chemically to both inorganic materials (e.g. glass, metals, fillers) and organic polymers (e.g. thermosets, thermoplastics, elastomers) thus functioning mainly as an efficient adhesion promoter and/or surface modifier.

Dynasytan® VTMOEO is a colorless, low-viscosity liquid with a typical aromatic odor.

### Safety and handling

Before considering the use of Dynasytan® products please read its Safety Data sheet (SDS) thoroughly for safety and toxicological data as well as for information on proper transportation, storage and use. The Safety Data Sheet is available after registration on our website [www.dynasytan.com](http://www.dynasytan.com) or upon request from your local representative, customer service or from Evonik Resource Efficiency GmbH, Product Safety Department, E-MAIL [sds-hu@evonik.com](mailto:sds-hu@evonik.com).

### Packaging, storage and shelf life

Dynasytan® VTMOEO is supplied in 25 kg containers, in 200 kg drums, or in 1.000 kg IBC one-way containers.

The containers must remain tightly sealed during storage and kept in a cool, well aired place. Product should be protected against humidity.

In the unopened container the shelf life of Dynasytan® VTMOEO is min. 12 months from delivery.

## Properties and applications

### 1. Adhesion promotion

Dynasylan® VTMOEO acts as an adhesion promoter for various mineral-filled polymers improving their mechanical and electrical properties, especially after exposure to moisture.

Once bonded to an inorganic filler, Dynasylan® VTMOEO hydrophobises the filler surface. This effect improves the compatibility of fillers with the polymer matrix, leading to a better dispersibility, reduced melt viscosity and easier processing of filled plastics. The principle of the adhesion promotion is shown below:

### 2. Dynasylan® VTMOEO as co-monomer for polymer dispersions

Polymer dispersions (e.g. styrene acrylics), modified with Dynasylan® VTMOEO show improved adhesion strength in wet conditions and wet scrub resistance.

### 3. Other applications

Dynasylan® VTMOEO can also be used as additive in organic coatings to improve adhesion on inorganic surfaces (metals, glass, ceramic surfaces), as well as for surface treatment of inorganic pigments.

## Reactivity

In the presence of moisture, the methoxy-ethoxy groups of Dynasylan® VTMOEO hydrolyze to produce 2-methoxyethanol and reactive silanol (Si-OH) groups which can bond to a variety of inorganic substrates. The vinyl functional end of Dynasylan® VTMOEO can react with a suitable polymer (activated by peroxide or radiation).

## Processing

### Toxicological and Environmental Aspects:

When exposed to moisture Dynasylan® VTMOEO liberates 2-methoxyethanol. This alcohol is suspected to be teratogenic, meaning that it is suspected to damage fertility or the unborn child. Evonik Industries AG offers a new generation of alternatives to vinyltris(2-methoxyethoxy)silane that do not liberate 2-methoxyethanol. In many applications these products perform even better than vinyltris(2-methoxy-ethoxy)-silane. More information about these alternatives is given in the Product Information for Dynasylan® 6490, Dynasylan® 6498 and Dynasylan® 6598.

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

**Europe/Middle-East/Africa/RoW**  
**Evonik Resource Efficiency GmbH**

Business Line Silanes  
Rodenbacher Chaussee 4  
63457 Hanau-Wolfgang  
Germany  
PHONE +49 6181 59 13636  
FAX +49 6181 59 713915  
dynasytan@evonik.com  
www.dynasytan.com

**Asia / Pacific**

**Evonik (SEA) Pte. Ltd.**

Business Line Silanes  
3 Internatioanl Business Park  
#07-18, Nordic European Centre  
Singapore 609927  
PHONE +65 6809 6576  
FAX +65 6809 6699  
dynasytan@evonik.com  
www.dynasytan.com

**Asia / Pacific**

**Evonik Japan Co. Ltd**

Business Line Silanes  
12th Floor Monolith Building  
2-3-1, Nishi-Shinjuku-ku  
Tokyo 163-0912  
Japan  
PHONE +81 353 23 7446  
FAX +81 353 23 7397  
dynasytan@evonik.com  
www.dynasytan.com

**North America**

**Evonik Corporation**

Business Line Silanes  
299 Jefferson Road  
Parsippany, NJ 07054-0677  
USA  
PHONE (TOLL FREE) +1 800 237 67 45  
PHONE +1 973 929 8513  
FAX +1 973 929 8503  
dynasytan@evonik.com  
www.dynasytan.com

**Asia / Pacific**

**Evonik Specialty**

**Chemicals (Shanghai) Co. Ltd.**

Business Line Silanes  
55, Chungdong Road  
Xinzhuang Industry Park  
Shanghai 201108  
P.R. China  
PHONE +86 21 61191-399  
FAX +86 21 61191-648  
dynasytan@evonik.com  
www.dynasytan.com

**Asia / Pacific**

**Evonik India Pvt. Ltd.**

Business Line Silanes  
Krislon House  
Saki Vihar Road, Anderi (E)  
Mumbai - 400 072  
India  
PHONE +91 226 7238 809  
FAX +91 226 7238 811  
dynasytan@evonik.com  
www.dynasytan.com

**North America**

**Silbond Corporation**

9901 Sand Creek Highway  
Weston, MI 49289  
USA  
PHONE +1 517 436 9316  
FAX +1 517 436 3148  
dynasytan@evonik.com  
www.dynasytan.com

**Asia / Pacific**

**Evonik Korea Ltd.**

Business Line Silanes  
94, Galsan 1-dong  
Bupyeong-gu  
Incheon, 403-081  
Korea  
PHONE +82 2320 4773  
FAX +82 2783 2520  
dynasytan@evonik.com  
www.dynasytan.com

**Latin America**

**Evonik Brasil Ltda.**

Business Line Silanes  
Alameda Campinas, 579  
01404-000 São Paulo-SP  
Brazil  
PHONE +55 11 3146 4123  
FAX +55 11 3146 4148  
dynasytan@evonik.com  
www.dynasytan.com

**Asia / Pacific**

**Evonik Taiwan Ltd.**

Business Line Silanes  
Artist Construction Bldg.  
9F, No. 133  
Min Sheng East Road, Sec 3  
Taipei, 105 Taiwan, R.O.C.  
Taiwan 10596  
PHONE +886 227 17 1242  
FAX +886 227 17 2106  
dynasytan@evonik.com  
www.dynasytan.com