

# Protectosil® 100 NK

## Water repellent formulation with water beading effect for mineral and hydroxyl-group containing substrates

### Technical Data

Properties and test methods	Value	Unit	Method
Density	approx. 0.88	g/cm <sup>3</sup>	DIN 51757
Boiling point	175 - 186	°C	DIN 51751
Flash point	> 57	°C	DIN 51755
Active ingredient content	97 - 100	%	-

### Registration

#### Protectosil® 100 NK

AICS (Australia):	Yes
DSL/NDSL (Canada):	No
PICCS (Philippines):	Yes
TSCA (USA):	Yes
IECS (P.R. China):	Yes
ENCS (Japan):	Yes
ECL (South Korea):	No
EINECS/ELINCS (EU):	Yes

Protectosil® 100 NK is suitable for waterproofing of porous mineral building materials.

An excellent beading effect develops on suitable substrates only a short time after application. Protectosil® 100 NK can be applied at full-strength or after dilution with suitable solvents.

### Safety and Handling

Before considering the use of Protectosil® products please read its Safety Data sheet (SDS) thoroughly for safety and toxicological data as well as for information on proper transportation, storage and use. The Safety Data Sheet is available on our website [www.protectosil.com](http://www.protectosil.com) or upon request from your local representative, customer service or from Evonik Resource Efficiency GmbH, Product Safety Department, E-MAIL [sds-hu@evonik.com](mailto:sds-hu@evonik.com).

### Packaging and Storage

Protectosil® 100 NK can be stored in originally sealed containers without any deterioration in quality for at least 6 months. The storage temperature are between -10 °C and 40 °C. Protectosil® 100 NK is available in 25 l, 205 l and 1.000 l.

## Properties and Use

### Suitable solvents:

- Ethanol\* (water free, denatured with petroleum hydrocarbons)
- Aliphatic hydrocarbon solvents (pentane, hexane, heptane, etc.)
- Aromatic hydrocarbon solvents (toluene, xylene)
- White spirit

Dilutions of from 1:1 to 1:9 are possible (Dilution of Protectosil® 100 NK and solvent)

\* recommended solvent

### Suitable porous, mineral substrates:

- Concrete (fresh or carbonated)
- Clinker masonry
- Ceramic tiles
- Sand-limestone
- Natural stone
- Cement render

### Product Characteristics

- solvent-free
- low volatility
- high reactivity
- very good beading effect
- water vaporpermeable, colorless impregnation
- seals hairline cracks up to 0.3 mm
- considerably reduces absorption of water and damaging water-borne salts (e.g. chlorides)
- very good penetration capacity
- very high alkali resistance
- stops the alkali-silica reaction

The substrates to be treated should be air-dry and clean in order to ensure deep penetration of the active ingredient. During application, the outside temperature and the temperature of the substrate should be in the range from 0 °C to 40 °C. The material should not be applied if there is strong wind or if it is raining. Protectosil® 100 NK must not come into contact with water either before or during use.

Protectosil® 100 NK must be applied by flow coating to the saturation point. This is achieved by allowing it to flow without pressure against the surface to be treated. All liquid delivery devices are suitable (airless spray guns, for example). The material must not be atomized.

Protectosil® 100 NK must remain in contact with the substrate for several seconds as a liquid film. Horizontal surfaces should have a shiny, wet appearance for 3-5 seconds. Vertical surfaces should exhibit a 30-50 cm shiny curtain of liquid.

## Application

All equipment and containers must be clean and dry. After use, they can be cleaned with any organic solvent (methylated spirit, petrol or thinners).

Non-absorbent substrates such as window frames, window sills, plastic fittings, window glass, etc., should be covered before application. Surfaces which accidentally come into contact with Protectosil® 100 NK can be cleaned with alcohol (spirit) or aqueous soap solution (the compatibility with the surface in question should be checked in advance). Cleaning should be carried out as quickly as possible (within a few hours), otherwise formation of a silicone resin film can make cleaning more difficult. Silicone resin films which have formed are best removed using ethanol (spirit).

Plants in the region of the surfaces to be treated should be protected against contact with Protectosil® 100 NK. Protectosil® 100 NK reacts with the interfaces in pores and capillaries of the mineral surface and forms invisible, water-repellent interfacial compounds. However, since it is frequently unknown whether the material has been previously treated, and the exact type of treatment, a test should always be performed on a small area to make sure that no undesired secondary phenomena occur.

### Application Details

Suitable substrates	Approximate consumption - Mode of application
Concrete	min. 150 g/m <sup>2</sup> - Low pressure pumping
Clinker masonry	min. 150 g/m <sup>2</sup> - Low pressure pumping
Ceramic tiles	approx. 100 g/m <sup>2</sup> - Low pressure pumping

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

#### **Europe / Middle-East / Africa / Row**

##### **Evonik Resource Efficiency GmbH**

Business Line Silanes  
Rodenbacher Chaussee 4  
63457 Hanau-Wolfgang  
Germany  
PHONE +49 6181 59 13636  
FAX +49 6181 59 713 915  
protectosil@evonik.com  
www.protectosil.com

#### **Asia / Pacific**

##### **Evonik (SEA) Pte. Ltd.**

Business Line Silanes  
3 Internatioanl Business Park  
#07-18, Nordic European Centre  
Singapore 609927  
PHONE +65 6809 6899  
FAX +65 6809 6699  
protectosil@evonik.com  
www.protectosil.com

#### **Asia / Pacific**

##### **Evonik Taiwan Ltd.**

Business Line Silanes  
Artist Construction Bldg  
9F, No. 133  
Min Sheng East Road, Sec 3  
Taipei, 105 Taiwan, R.O.C.  
Taiwan 10596  
PHONE +886 227 17 1242  
FAX +886 227 17 2106  
protectosil@evonik.com  
www.protectosil.com

#### **North America**

##### **Evonik Corporation**

Business Line Silanes  
299 Jefferson Road  
Parsippany, NJ 07054-0677  
USA  
PHONE (TOLL FREE) +1 800 828 0919  
FAX +1 973 929 8503  
protectosil@evonik.com  
www.protectosil.com

#### **Asia / Pacific**

##### **Evonik (Shanghai) Co. Ltd.**

Business Line Silanes  
55, Chungdong Road  
Shanghai 201108  
P.R. China  
PHONE +86 21 6119 1660  
FAX +86 21 6119 1075  
protectosil@evonik.com  
www.protectosil.com

#### **Asia / Pacific**

##### **Evonik Japan Co. Ltd**

Business Line Silanes  
12th Floor Monolith Building  
2-3-1, Nishi-Shinjuku-ku  
Tokyo 163-0912  
Japan  
PHONE +81 353 23 7446  
FAX +81 353 23 7397  
protectosil@evonik.com  
www.protectosil.com

#### **Latin America**

##### **Evonik Brasil Ltda.**

Business Line Silanes  
Alameda Campinas, 579  
01404-000 São Paulo-SP  
Brazil  
PHONE +55 11 3146 4123  
FAX +55 11 3146 4148  
protectosil@evonik.com  
www.protectosil.com

#### **Asia / Pacific**

##### **Evonik Korea Ltd.**

Business Line Silanes  
94, Galsan 1-dong  
Bupyeong-gu  
Incheon, 403-081, Korea  
PHONE +82 2320 4778  
FAX +82 2783 2520  
protectosil@evonik.com  
www.protectosil.com

#### **Asia / Pacific**

##### **Evonik India Pvt. Ltd.**

Business Line Silanes  
Krislon House  
Saki Vihar Road, Anderi (E)  
Mumbai - 400 072  
India  
PHONE +91 226 7238 809  
FAX +91 226 7238 811  
protectosil@evonik.com  
www.protectosil.com