

# Protectosil® 60 SK

## High performance water-repellent with water beading effect for masonry

### Technical Data

Properties and test methods	Value	Unit	Method
Flash point	> 40	°C	DIN EN ISO 2719
Active ingredient content	approx. 100	%	-
Density	approx. 1.038	g/cm <sup>3</sup>	DIN 51757
Appearance	yellowish, clear to slightly turbid	-	-
Viscosity (20 °C)	approx. 30	mPa·s	DIN 53015

### Registration

#### Protectosil® 60 SK

EINECS/ELINCS (EU):	Yes
DSL/NDSL (Canada):	*
PICCS (Philippines):	Yes
TSCA (USA):	Yes
IECS (P.R. China):	*
ENCS (Japan):	Yes
ECL (South Korea):	Yes
AICS (Australia):	No
* = Information upon request	

High performance water-repellent with water beading effect for masonry

Protectosil® 60 SK is a free-flowing yellowish clear to slightly turbid almost odourless, slightly alcoholic frost resistant liquid based on a silane/siloxane. Protectosil® 60 SK is free of tinorganic compounds. Protectosil® 60 SK can be applied at full-strength or after dilution with suitable solvents, such as ethanol or white spirit.

### Safety and Handling

Before considering the use of Protectosil® products please read its Safety Data sheet (SDS) thoroughly for safety and toxicological data as well as for information on proper transportation, storage and use. The Safety Data Sheet is available after registration on our website [www.protectosil.com](http://www.protectosil.com) or upon request from your local representative, customer service or from Evonik Operations GmbH, Product Safety Department, E-MAIL [sds-hu@evonik.com](mailto:sds-hu@evonik.com).

### Packaging and Storage

Provided that moisture is excluded, Protectosil® 60 SK has a shelf life of at least 12 months from delivery. Protectosil® 60 SK is supplied in 25 l PE canisters and 200 l plastic lined steel drums and 1.000 l container. The material should be stored at temperatures between -10 and 40 °C (best between 0 °C and 30 °C).

## Properties and Use

Protectosil® 60 SK is suitable for waterproofing porous mineral building materials, such as concrete, sand limestone, clinker masonry and mineral based natural stone. An excellent beading effect develops a short time after application.

### Product Properties

- low volatility
- high reactivity
- very good beading effect
- water vapor-permeable, colorless impregnation
- seals hairline cracks up to 0.3 mm
- considerably reduces absorption of water and damaging water-borne salts (e.g. chlorides)
- high alkali resistance

### Directions for use:

Untreated substrates should be air-dry and clean in order to ensure deep penetration of the active ingredient. During application the outside temperature as well as the substrate's temperature should be between 5 and 40 °C. The material should not be applied during strong wind or if it is raining. The material must not come into contact with water either before or during use. All surfaces must be cleaned to remove all traces of dirt, dust, efflorescence, mold, salt, grease, oil, asphalt, laitance, curing compounds, paint, coatings and other foreign materials. Acceptable surface cleaning methods include sandblasting, water blasting and chemical cleaners. Protectosil® 60 SK cannot be applied to a painted surface. The mineral groups of the substrate must be accessible for the product to create a strong bonding, which is essential for good long-term performance. Protectosil® 60 SK should be applied using low pressure pumping equipment with a wet fan type spray nozzle. Do not apply to a wet or damp substrate. On vertical surfaces apply the Protectosil® 60 SK in a flooding application, so the material runs down 6 to 8 inches (15-20 cm) below the spray pattern. On horizontal surfaces the liquid material should pond on the surface for at least 5 seconds before being absorbed. A test patch should be applied to the substrate to verify coverage rate and application conditions. Protect glass, metal, plastic and other nonporous substrates from over spray Protectosil® 60 SK will not etch glass, but will leave a residue on nonporous surfaces. The material must not be atomized. Protectosil® 60 SK can be applied at full-strength or after dilution with suitable solvents. We recommend a minimum application concentration of 10% by weight (which corresponds to 1 part Protectosil® 60 SK and 9 parts solvent). It is not recommended to use the product at full-strength on concrete. Here it is of advantage to use dilution rates ranging from 1:3 up to 1:9.

## Processing

### Suitable solvents are:

- Ethanol water free\* (denatured with petroleum hydrocarbons)
- Aliphatic hydrocarbon solvents (pentane, hexane, heptane, etc.)
- Aromatic hydrocarbon solvents (toluene, xylene)
- White spirit

\* highly recommended solvent

The amount to be applied depends on how porous the substrate is. When using a dilution rate of 1:9 in ethanol, coverage rates range from 0.2 - 0.7 l/m<sup>2</sup> for mineral plaster facades, 0.2 - 0.8 l/m<sup>2</sup> for sand lime stone, 0.25 - 1.0 l/m<sup>2</sup> for brick and 0.17 - 0.6 l/m<sup>2</sup> for concrete. A test patch must be applied to determine the correct coverage rate. In order to reach these consumption rates it may be necessary to apply the material using multiple applications steps. It is recommended to let the surface dry between every application step. The performance of Protectosil® 60 SK, (e.g. evaluated by the reduction of water up-take) depends on both the dilution rate and the consumption rate. The above mentioned consumption rates are required in order to achieve reduction of water up-take greater than 90%. If a reduction of water up-take lower than that is required then a higher dilution rate (e.g. 1:14 in ethanol) or a smaller consumption rate is possible to use. This should be evaluated in previous tests.

All equipment and containers must be clean and dry. After use, they can be cleaned with any organic solvent (methylated spirit or petrol). Non-absorbent substrates such as window frames, window sills, plastic fittings, window glass, etc., should be covered before application. Surfaces which accidentally come into contact with Protectosil® 60 SK can be cleaned with alcohol (spirit) or aqueous soap solution. Cleaning should be carried out as quickly as possible (within a few hours), otherwise formation of a silicone resin film can make cleaning more difficult. Silicone resin films are best removed using ethanol (or spirit). Plant life should be protected from overspray. Protectosil® 60 SK reacts with the interfaces in pores and capillaries of the mineral surface and forms invisible, water-repellent interfacial compounds. However, since it is frequently unknown whether the material has been previously treated, and the exact type of treatment, a test should always be performed on a small area to make sure that no undesired secondary phenomena occur.

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

**Europe / Middle-East / Africa**

**Evonik Operations GmbH**

Silanes Business Line  
Rodenbacher Chaussee 4  
63457 Hanau-Wolfgang  
Germany  
FAX +49 6181 59 713 915  
protectosil@evonik.com  
www.protectosil.com

**Asia / Pacific**

**Evonik (SEA) Pte. Ltd.**

Silanes Business Line  
3 Internatioanl Business Park  
#07-18, Nordic European Centre  
Singapore 609927  
PHONE +65 6809 6906  
FAX +65 6809 6699  
protectosil@evonik.com  
www.protectosil.com

**Asia / Pacific**

**Evonik Taiwan Ltd.**

Silanes Business Line  
Artist Construction Bldg  
9F, No. 133  
Min Sheng East Road, Sec 3  
Taipei, 105 Taiwan, R.O.C.  
Taiwan 10596  
PHONE +886 227 17 1242 #247  
FAX +886 227 17 2106  
protectosil@evonik.com  
www.protectosil.com

**North America**

**Evonik Corporation**

Silanes Business Line  
299 Jefferson Road  
Parsippany, NJ 07054  
USA  
PHONE (TOLL FREE) +1 800 828 0919  
protectosil@evonik.com  
www.protectosil.com

**Asia / Pacific**

**Evonik (Shanghai) Co. Ltd.**

Silanes Business Line  
55, Chungdong Road  
Shanghai 201108  
P.R. China  
PHONE +86 21 6119 1660  
FAX +86 21 6119 1075  
protectosil@evonik.com  
www.protectosil.com

**Asia / Pacific**

**Evonik Japan Co. Ltd**

Silanes Business Line  
12th Floor Monolith Building  
2-3-1, Nishi-Shinjuku-ku  
Tokyo 163-0912  
Japan  
PHONE +81 353 23 7446  
FAX +81 353 23 7397  
protectosil@evonik.com  
www.protectosil.com

**Region Central and South America**

**Evonik Brasil Ltda.**

Silanes Business Line  
Rua Arquiteto Olavo Redig de Campos, 105  
Torre A - 04711-904 São Paulo- SP  
Brazil  
PHONE +55 11 3146 9627  
protectosil@evonik.com  
www.protectosil.com

**Asia / Pacific**

**Evonik Korea Ltd.**

Silanes Business Line  
3F (Nongshim Sungmookwan B/D)  
112 Yeouidaebang-Ro  
Dongjak-Gu  
Seoul, 07057  
Korea  
PHONE +82 2320 4778  
FAX +82 2783 2520  
protectosil@evonik.com  
www.protectosil.com

**Asia / Pacific**

**Evonik India Pvt. Ltd.**

Silanes Business Line  
Krislon House  
Saki Vihar Road, Anderi (E)  
Mumbai - 400 072  
India  
PHONE +91 226 7238 809  
FAX +91 226 7238 811  
protectosil@evonik.com  
www.protectosil.com