

VP Disp. W 640 XC8

Developmental anionic dispersion of fumed aluminium oxide*

Characteristic physico-chemical data

Properties and test methods	Unit	Value
Al ₂ O ₃ - content measured as residue on ignition	wt. %	37 ± 1.0
pH DIN EN ISO 787/9		7.0 - 10.0
Viscosity measured according to DIN EN ISO 3219 at a shear rate of 100 s ⁻¹	mPas	≤ 2000
Mean aggregate size d-50 value	µm	0.08
Sodium content measured as Na by ICP	wt. %	approx. 0.5
Density 20 °C	g/cm ³	1.35

The data represent typical values (no product specification).

Registrations (substance or product components)

VP Disp. W 640 XC8

CAS-No.*	1344-28-1
EINECS (Europe), TSCA (USA), DSL (Canada), AICS (Australia), ENCS (Japan), IECSC (China), KECI (Korea)	All components of this dispersion are listed in the mentioned inventories.

*Data refer to the inorganic substance used

VP Disp. W 640 XC8 is an alumina dispersion with a high solid content, special anionic stabilization and a neutral to basic pH.

Applications and properties

Applications

- Ready-to-use binder for investment casting. Especially suitable for casting of titanium alloys (e.g. titanium aluminate). Slurries prepared with yttria, alumina and zirconia powders show excellent stability over several months
- Ceramic applications
- Applications that require anionic surface charge and/or neutral to basic pH

Properties

- Contains wetting agent to improve wettability of wax
- Contains polymer to increase shell green strength
- Anionic (negative) surface charge as a result of special stabilization
- High solid content
- Superior rheological behavior
- Easy to handle

Appearance

- VP Disp. W 640 XC8 is a milky-white, water-based liquid.

* Developmental products are labeled with the VP designation. Commercialization depends on market response.

Safety and handling

Information concerning the safety of this product is listed in the corresponding Safety Data Sheet, which will be sent with the first delivery or upon updating. Such information is also available from Evonik Operations, Product Safety Department, E-MAIL sds-im@evonik.com We recommend to read carefully the safety data sheet prior to the use of our product.

Packaging and storage

Depending on the region, VP Disp. W 640 XC8 is available in 60 kg containers, 250 kg drums and 1.250 kg intermediate bulk containers (IBC's). Storage temperature: 5 to 50 °C. The product should be used within 12 months from the date of production. Small amounts of sedimentation are normal.

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

Customer Service

**Europe/ Middle-East/
Africa/ Latin America**
Evonik Operations GmbH
Business Line Silica
PB 010-A410
Rodenbacher Chaussee 4
63457 Hanau-Wolfgang
Germany
PHONE +49 6181 59 12532
FAX +49 6181 59 712532
aerosil@evonik.com
www.silica-specialist.com

North America
Evonik Corporation
Business Line Silica
299 Jefferson Road
Parsippany, NJ 07054-0677
USA
PHONE +1 800-233-8052
FAX +1 973-929-8502
aerosil@evonik.com
www.silica-specialist.com

Asia (excluding Japan)
Evonik (SEA) Pte. Ltd.
Business Line Silica
3 International Business Park
Nordic European Centre, #07-18
Singapore 609927
PHONE +65 6809-6877
FAX +65 6809-6677
aerosil@evonik.com
www.silica-specialist.com

Japan
NIPPON AEROSIL CO., LTD.
Marketing & Sales Division
P.O. Box 7015
Shinjuku Monolith 13F
3-1, Nishi-Shinjuku 2-chrome
Shinjuku-ku, Tokyo
163-0913 Japan
PHONE +81 3 3342-1789
FAX +81 3 3342-1761
infonac@evonik.com
www.aerosil.jp

Technical Service

**Europe/ Middle-East/
Africa/ Latin America**
Evonik Operations
Business Line Silica
HPC 911-221 A
Rodenbacher Chaussee 4
63457 Hanau-Wolfgang
Germany
PHONE +49 6181 59-3936
FAX +49 6181 59 4489
technical.service.aerosil@
evonik.com
www.silica-specialist.com

North America
Evonik Corporation
Business Line Silica
2 Turner Place
Piscataway, NJ 08855-0365
USA
PHONE +1 888 SILICAS
PHONE +1 732 981-5000
FAX +1 732 981-5275
technical.service.aerosil@
evonik.com
www.silica-specialist.com

Asia (excluding Japan)
**Evonik Specialty
Chemicals (Shanghai) Co.,Ltd**
Business Line Silica
55 Chundong Road
Xinzhuang Industry Park
Shanghai 201108
P.R. China
PHONE +86 21 6119-1151
FAX +86 21 6119-1075
technical.service.aerosil@
evonik.com
www.silica-specialist.com

Japan
NIPPON AEROSIL CO., LTD.
Applied Technology Group
3 Mita-Cho
Yokkaichi, Mie
510-0841 Japan
PHONE +81 59 345-5270
FAX +81 59 346-4657
infonac@evonik.com
www.aerosil.jp