

# VPS SIVO 280

## Modified organofunctional silane oligomer

### Technical data

Properties and test methods	Value	Unit	Method
Density (20 °C)	approx. 1.15	g/cm <sup>3</sup>	DIN 51757
Flash point	> 95	°C	EN 22719
Viscosity (20 °C)	< 3.000	mPa·s	DIN 53015
Physical form	colorless to light yellowish	-	-

VPS SIVO 280 is a novel multifunctional siloxane adhesion promoter with aminofunctionalities that can be used for various applications.

VPS SIVO 280 is mainly dedicated for use in adhesives & sealants to improve the adhesion of hybrid products (e.g. silylated polyurethanes, MS Polymers®) and RTV-silicones - especially to difficult to stick polymethylmethacrylate (PMMA) substrates. In addition, VPS SIVO 280 can lead to adequate adhesive cure and it imparts both additional flexibility and hydrophobicity.

### Registrations

#### VPS SIVO 280

EINECS/ELINCS (EU):	Yes
AICS (Australia):	*
DSL/NDSL (Canada):	*
PICCS (Philippines):	*
TSCA (USA):	Yes
IECSC (P.R. China):	*
ENCS (Japan):	*
ECL (South Korea):	*
REACH (Europe)	Exempted
* = information upon request	

### Our recommendations:

VPS SIVO 280 has been developed mainly for use in:

- MS Polymer®
- Silane modified polyurethane/ polyether
- RTV-1/RTV-2 silicones
- Butyl rubber

We do not recommend to use VPS SIVO 280 in 1K-PU or 1K-EP formulations. The compatibility of other ingredients with VPS SIVO 280 should be tested in advance.

### Key Benefits

VPS SIVO 280 exhibits excellent wetting on substrates and it can form weather- and moisture-resistant bonds to substrates which are partially difficult to adhere. The main benefits of VPS SIVO 280 in silylated polyurethane or MS polymer based adhesives & sealants are:

- Improved adhesion to plastics, especially to polymethylmethacrylate (PMMA)
- Improved adhesion to aluminum
- Well-Balanced mechanical properties
- Significant VOC-reduction compared to conventional amino silanes

### Properties and applications

VPS SIVO 280 is a versatile product that provides improved product performance and quality. VPS SIVO 280 is soluble in alcohols, aliphatic and aromatic hydrocarbons, but it can undergo reactions with ketones or ester solvents. VPS SIVO 280 is considered primarily as an additive in moisture curable adhesives & sealants to eliminate the need for special primers in numerous bonding applications. Loading levels of 0,5 to 2,0 wt. % of VPS SIVO 280 as an additive - calculated on the overall formulation - are typically recommended.

### Safety and handling

Before considering the use of VPS SIVO 280 please read its Safety Data sheet (SDS) thoroughly for safety and toxicological data as well as for information on proper transportation, storage and use. The Safety Data Sheet is available after registration on our website [www.dynasytan.com](http://www.dynasytan.com) or upon request from your local representative, customer service or from Evonik Resource Efficiency GmbH, Product Safety Department, E-MAIL [sds-hu@evonik.com](mailto:sds-hu@evonik.com).

### Packaging, storage and shelf life

VPS SIVO 280 is available in 25 kg pails, 200 kg drums and 1.000 kg IBC's.

The shelf life of VPS SIVO 280 is min. 9 months from delivery.

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

**Europe/Middle-East/Africa/RoW**

**Evonik Resource Efficiency GmbH**

Business Line Silanes  
Rodenbacher Chaussee 4  
63457 Hanau-Wolfgang  
Germany  
PHONE +49 6181 59 13636  
FAX +49 6181 59 713915  
dynasytan@evonik.com  
www.dynasytan.com

**Asia / Pacific**

**Evonik (SEA) Pte. Ltd.**

Business Line Silanes  
3 Internatioanl Business Park  
#07-18, Nordic European Centre  
Singapore 609927  
PHONE +65 6809 6576  
FAX +65 6809 6699  
dynasytan@evonik.com  
www.dynasytan.com

**Asia / Pacific**

**Evonik Japan Co. Ltd**

Business Line Silanes  
12th Floor Monolith Building  
2-3-1, Nishi-Shinjuku-ku  
Tokyo 163-0912  
Japan  
PHONE +81 353 23 7446  
FAX +81 353 23 7397  
dynasytan@evonik.com  
www.dynasytan.com

**North America**

**Evonik Corporation**

Business Line Silanes  
299 Jefferson Road  
Parsippany, NJ 07054-0677  
USA  
PHONE (TOLL FREE) +1 800 237 67 45  
PHONE +1 973 929 8513  
FAX +1 973 929 8503  
dynasytan@evonik.com  
www.dynasytan.com

**Asia / Pacific**

**Evonik Specialty  
Chemicals (Shanghai) Co. Ltd.**

Business Line Silanes  
55, Chungdong Road  
Xinzhuang Industry Park  
Shanghai 201108  
P.R. China  
PHONE +86 21 61191-399  
FAX +86 21 61191-648  
dynasytan@evonik.com  
www.dynasytan.com

**Asia / Pacific**

**Evonik India Pvt. Ltd.**

Business Line Silanes  
Krislon House  
Saki Vihar Road, Anderi (E)  
Mumbai - 400 072  
India  
PHONE +91 226 7238 809  
FAX +91 226 7238 811  
dynasytan@evonik.com  
www.dynasytan.com

**North America**

**Silbond Corporation**

9901 Sand Creek Highway  
Weston, MI 49289  
USA  
PHONE +1 517 436 9316  
FAX +1 517 436 3148  
dynasytan@evonik.com  
www.dynasytan.com

**Asia / Pacific**

**Evonik Korea Ltd.**

Business Line Silanes  
94, Galsan 1-dong  
Bupyeong-gu  
Incheon, 403-081  
Korea  
PHONE +82 2320 4773  
FAX +82 2783 2520  
dynasytan@evonik.com  
www.dynasytan.com

**Latin America**

**Evonik Brasil Ltda.**

Business Line Silanes  
Alameda Campinas, 579  
01404-000 São Paulo-SP  
Brazil  
PHONE +55 11 3146 4123  
FAX +55 11 3146 4148  
dynasytan@evonik.com  
www.dynasytan.com

**Asia / Pacific**

**Evonik Taiwan Ltd.**

Business Line Silanes  
Artist Construction Bldg.  
9F, No. 133  
Min Sheng East Road, Sec 3  
Taipei, 105 Taiwan, R.O.C.  
Taiwan 10596  
PHONE +886 227 17 1242  
FAX +886 227 17 2106  
dynasytan@evonik.com  
www.dynasytan.com